



LNP™ STAT-KON™ Compound DEL339XF

Americas: COMMERCIAL

Also known as: LNP™ STAT-KON™ Compound DCL-4033 FR

Product reorder name: DEL339XF

LNP STAT-KON DEL339XF is a compound based on Polycarbonate resin containing 15% Carbon Fiber, 15% PTFE. Added features include: Electrically Conductive, Flame Retardant, Wear Resistant.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yield	1160	kgf/cm ²	ASTM D 638
Tensile Stress, break	1160	kgf/cm ²	ASTM D 638
Tensile Strain, yield	1.8	%	ASTM D 638
Tensile Strain, break	1.8	%	ASTM D 638
Tensile Modulus, 50 mm/min	105400	kgf/cm ²	ASTM D 638
Flexural Stress	1820	kgf/cm ²	ASTM D 790
Flexural Modulus	91300	kgf/cm ²	ASTM D 790
Tensile Stress, yield	112	MPa	ISO 527
Tensile Stress, break	112	MPa	ISO 527
Tensile Strain, yield	1.6	%	ISO 527
Tensile Strain, break	1.6	%	ISO 527
Tensile Modulus, 1 mm/min	10950	MPa	ISO 527
Flexural Stress	164	MPa	ISO 178
Flexural Modulus	9500	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	36	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	5	cm-kgf/cm	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	130	cm-kgf	ASTM D 3763
Multiaxial Impact	34	cm-kgf	ISO 6603
Izod Impact, unnotched 80*10*4 +23°C	24	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	5	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	141	°C	ASTM D 648



LNP™ STAT-KON™ Compound DEL339XF

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	140	°C	ASTM D 648
CTE, -40°C to 40°C, flow	6.3E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	1.44E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	6.2E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	1.4E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	142	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	141	°C	ISO 75/Af
PHYSICAL			
Density	1.39	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.1	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.2 - 0.4	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	0.3 - 0.5	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs (5)	0.31	%	ISO 294
Mold Shrinkage, xflow, 24 hrs (5)	0.4	%	ISO 294
Density	1.38	g/cm ³	ISO 1183
ELECTRICAL			
Surface Resistivity	1.E+07 - 1.E+09	Ohm	ASTM D 257



LNP™ STAT-KON™ Compound DEL339XF

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120	°C
Drying Time	4	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	305 - 325	°C
Front - Zone 3 Temperature	320 - 330	°C
Middle - Zone 2 Temperature	310 - 320	°C
Rear - Zone 1 Temperature	295 - 305	°C
Mold Temperature	80 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm