



LNP™ STAT-KON™ Compound DX02437

Asia Pacific: COMMERCIAL

LNP Stat-Kon DX02437 is a compound based on Polycarbonate resin containing conductive carbon powder, with good impact-resistance, flow and ESD performance, suitable for semi-con industry.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	590	kgf/cm ²	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	470	kgf/cm ²	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	19.3	%	ASTM D 638
Tensile Modulus, 5 mm/min	26100	kgf/cm ²	ASTM D 638
Tensile Stress, yield, 5 mm/min	58	MPa	ISO 527
Tensile Stress, break, 5 mm/min	47	MPa	ISO 527
Tensile Strain, break, 5 mm/min	16.5	%	ISO 527
Tensile Modulus, 1 mm/min	2550	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	92	MPa	ISO 178
Flexural Stress, break, 2 mm/min	90	MPa	ISO 178
Flexural Strain, break, 2 mm/min	7.8	%	ISO 178
Flexural Modulus, 2 mm/min	2550	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	218	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	36	cm-kgf/cm	ASTM D 256
Izod Impact, notched, 0°C	29	cm-kgf/cm	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	275	cm-kgf	ASTM D 3763
Multiaxial Impact	643	cm-kgf	ISO 6603
Instrumented Impact Total Energy, 23°C	398	cm-kgf	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	130	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	24	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 0°C	20	kJ/m ²	ISO 180/1A



LNP™ STAT-KON™ Compound DX02437

Asia Pacific: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
IMPACT			
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	26	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	95	kJ/m ²	ISO 179/1eU
THERMAL			
Vicat Softening Temp, Rate A/50	144	°C	ASTM D 1525
HDT, 1.82 MPa, 3.2 mm	111	°C	ASTM D 648
Vicat Softening Temp, Rate A/50	144	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	126	°C	ISO 75/Af
PHYSICAL			
Density	1.236	g/cm ³	ASTM D 792
Mold Shrinkage, flow, 1.5-3.2 mm (5)	0.64	%	SABIC Method
Mold Shrinkage, xflow, 1.5-3.2 mm (5)	0.68	%	SABIC Method
Melt Volume Rate, MVR at 300°C/5.0 kg	16	cm ³ /10 min	ISO 1133
ELECTRICAL			
Volume Resistivity	1.41E+07	Ohm-cm	ASTM D 257
Surface Resistivity	4.8E+07	Ohm	ASTM D 257



LNP™ STAT-KON™ Compound DX02437

Asia Pacific: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120	°C
Drying Time	4	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	305 - 325	°C
Front - Zone 3 Temperature	320 - 330	°C
Middle - Zone 2 Temperature	310 - 320	°C
Rear - Zone 1 Temperature	295 - 305	°C
Mold Temperature	80 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm