



LNP™ STAT-KON™ Compound DX03571

Americas: COMMERCIAL

Also known as: LNP™ STAT-KON™ Compound PDX-D-03571

Product reorder name: DX03571

LNP STAT-KON DX03571 is a compound based on Polycarbonate resin containing Proprietary Filler(s). Added features of this material include: Electrically Conductive.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, break	610	kgf/cm ²	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	610	kgf/cm ²	ASTM D 638
Tensile Strain, break	4	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	4	%	ASTM D 638
Tensile Modulus, 50 mm/min	29500	kgf/cm ²	ASTM D 638
Flexural Stress	980	kgf/cm ²	ASTM D 790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	980	kgf/cm ²	ASTM D 790
Flexural Modulus	28800	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	28800	kgf/cm ²	ASTM D 790
IMPACT			
Izod Impact, unnotched, 23°C	108	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	5	cm-kgf/cm	ASTM D 256
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	121	°C	ASTM D 648
PHYSICAL			
Density	1.26	g/cm ³	ASTM D 792
ELECTRICAL			
Volume Resistivity	1.E+02 - 1.E+04	Ohm-cm	ASTM D 257
Surface Resistivity	1.E+02 - 1.E+04	Ohm	ASTM D 257



LNP™ STAT-KON™ Compound DX03571

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120	°C
Drying Time	4	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	305 - 325	°C
Front - Zone 3 Temperature	320 - 330	°C
Middle - Zone 2 Temperature	310 - 320	°C
Rear - Zone 1 Temperature	295 - 305	°C
Mold Temperature	80 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm