



LNP™ STAT-KON™ Compound DX04490

Americas: COMMERCIAL

Also known as: LNP™ STAT-KON™ Compound PDX-D-04490

Product reorder name: DX04490

LNP STAT-KON DX04490 is a compound based on Polycarbonate resin containing Proprietary Filler(s). Added feature of this grade is: Electrically Conductive.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yield	610	kgf/cm ²	ASTM D 638
Tensile Stress, break	540	kgf/cm ²	ASTM D 638
Tensile Strain, yield	4.2	%	ASTM D 638
Tensile Strain, break	16.3	%	ASTM D 638
Tensile Modulus, 50 mm/min	30400	kgf/cm ²	ASTM D 638
Flexural Stress	910	kgf/cm ²	ASTM D 790
Flexural Modulus	27700	kgf/cm ²	ASTM D 790
Tensile Stress, yield	61	MPa	ISO 527
Tensile Stress, break	54	MPa	ISO 527
Tensile Strain, yield	4.5	%	ISO 527
Tensile Strain, break	8.5	%	ISO 527
Tensile Modulus, 1 mm/min	2710	MPa	ISO 527
Flexural Stress	75	MPa	ISO 178
Flexural Modulus	2510	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	238	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	4	cm-kgf/cm	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	43	cm-kgf	ASTM D 3763
Multiaxial Impact	96	cm-kgf	ISO 6603
Izod Impact, unnotched 80*10*4 +23°C	167	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	5	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	132	°C	ASTM D 648



LNP™ STAT-KON™ Compound DX04490

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
CTE, -40°C to 40°C, flow	6.3E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	5.94E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	6.35E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	6.08E-05	1/°C	ISO 11359-2
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	133	°C	ISO 75/Af
PHYSICAL			
Density	1.23	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.2	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.4	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	0.5	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs (5)	0.42	%	ISO 294
Mold Shrinkage, xflow, 24 hrs (5)	0.5	%	ISO 294
Density	1.23	g/cm ³	ISO 1183
ELECTRICAL			
Volume Resistivity	1.E+02 - 1.E+05	Ohm-cm	ASTM D 257
Surface Resistivity	1.E+02 - 1.E+05	Ohm	ASTM D 257



LNP™ STAT-KON™ Compound DX04490

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120	°C
Drying Time	4	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	305 - 325	°C
Front - Zone 3 Temperature	320 - 330	°C
Middle - Zone 2 Temperature	310 - 320	°C
Rear - Zone 1 Temperature	295 - 305	°C
Mold Temperature	80 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm