



LNP™ STAT-KON™ Compound DX91077

Americas: COMMERCIAL

Also known as: LNP™ STAT-KON™ Compound PDX-D-91077

Product reorder name: DX91077

LNP STAT-KON DX91077 is a compound based on Polycarbonate resin containing Proprietary Filler(s). Added features of this grade include: Electrically Conductive, Impact Modified.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	570	kgf/cm ²	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	450	kgf/cm ²	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	4.8	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	15	%	ASTM D 638
Tensile Modulus, 50 mm/min	27600	kgf/cm ²	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	950	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	28100	kgf/cm ²	ASTM D 790
Tensile Stress, yield, 5 mm/min	55	MPa	ISO 527
Tensile Stress, break, 5 mm/min	48	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	4.8	%	ISO 527
Tensile Strain, break, 5 mm/min	12.4	%	ISO 527
Tensile Modulus, 1 mm/min	2600	MPa	ISO 527
Flexural Stress	84	MPa	ISO 178
Flexural Modulus, 2 mm/min	2580	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	177	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	7	cm-kgf/cm	ASTM D 256
Multiaxial Impact	285	cm-kgf	ISO 6603
Instrumented Impact Total Energy, 23°C	316	cm-kgf	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	125	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	11	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	139	°C	ASTM D 648



LNP™ STAT-KON™ Compound DX91077

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	130	°C	ASTM D 648
CTE, -30°C to 30°C, flow	6.58E+01	1/°C	ASTM D 696
CTE, -30°C to 30°C, xflow	6.71E+01	1/°C	ASTM D 696
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	140	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	127	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.23	-	ASTM D 792
Density	1.23	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.14	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.8 - 1	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	1 - 3	%	ASTM D 955
Moisture Absorption (23°C / 50% RH)	0.24	%	ISO 62
ELECTRICAL			
Surface Resistivity	4.E+00 - 6.E+00	Ohm	ASTM D 257



LNP™ STAT-KON™ Compound DX91077

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120	°C
Drying Time	4	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	305 - 325	°C
Front - Zone 3 Temperature	320 - 330	°C
Middle - Zone 2 Temperature	310 - 320	°C
Rear - Zone 1 Temperature	295 - 305	°C
Mold Temperature	80 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm