



LNP* Stat-kon* Compound DEL339XC

Asia Pacific: COMMERCIAL

Also known as: LNP* Stat-kon* Compound DCL-4033 FR HP

Product reorder name: DEL339XC

LNP STAT-KON* DEL339XC is a compound based on Polycarbonate resin containing Carbon Fiber, Flame Retardant, PTFE. Added features of this material include: Electrically Conductive.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	UNIT	STANDARD
MECHANICAL			
Tensile Stress, break	1320	kgf/cm ²	ASTM D 638
Tensile Strain, break	2	%	ASTM D 638
Tensile Modulus, 50 mm/min	146200	kgf/cm ²	ASTM D 638
Flexural Stress	1990	kgf/cm ²	ASTM D 790
Flexural Modulus	114500	kgf/cm ²	ASTM D 790
Tensile Stress, break	129	MPa	ISO 527
Tensile Strain, break	1.8	%	ISO 527
Tensile Modulus, 1 mm/min	12700	MPa	ISO 527
Flexural Stress	200	MPa	ISO 178
Flexural Modulus	12400	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	49	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	7	cm-kgf/cm	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	124	cm-kgf	ASTM D 3763
Multiaxial Impact	26	cm-kgf	ISO 6603
Izod Impact, unnotched 80*10*4 +23°C	29	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	8	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	150	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	145	°C	ASTM D 648
CTE, -40°C to 40°C, flow	3.47E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	3.94E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	3.47E-05	1/°C	ISO 11359-2



LNP* Stat-kon* Compound DEL339XC

Asia Pacific: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	UNIT	STANDARD
THERMAL			
CTE, -40°C to 40°C, xflow	3.94E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	149	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	145	°C	ISO 75/Af
PHYSICAL			
Density	1.37	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.1	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs	0.1	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs	0.4	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs	0.05	%	ISO 294
Mold Shrinkage, xflow, 24 hrs	0.44	%	ISO 294
Density	1.37	g/cm ³	ISO 1183
ELECTRICAL			
Surface Resistivity	1.E+01 - 1.E+06	Ohm	ASTM D 257



LNP* Stat-kon* Compound DEL339XC

Asia Pacific: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	UNIT
Injection Molding		
Drying Temperature	120	°C
Drying Time	4	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	305 - 325	°C
Front - Zone 3 Temperature	320 - 330	°C
Middle - Zone 2 Temperature	310 - 320	°C
Rear - Zone 1 Temperature	295 - 305	°C
Mold Temperature	80 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm