



LNP™ THERMOCOMP™ Compound DF0029ER

Americas: COMMERCIAL

Also known as: LNP™ THERMOCOMP™ Compound DF-1002 EM FR MR

Product reorder name: DF0029ER

LNP THERMOCOMP DF0029ER is a compound based on Polycarbonate resin containing 10% Glass Fiber. Added features of this material include: Easy Molding, Mold Release, Flame Retardant.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yield	850	kgf/cm ²	ASTM D 638
Tensile Stress, break	800	kgf/cm ²	ASTM D 638
Tensile Strain, yield	3.9	%	ASTM D 638
Tensile Strain, break	5.5	%	ASTM D 638
Tensile Modulus, 50 mm/min	42100	kgf/cm ²	ASTM D 638
Flexural Modulus	42100	kgf/cm ²	ASTM D 790
Tensile Stress, yield	84	MPa	ISO 527
Tensile Stress, break	81	MPa	ISO 527
Tensile Strain, yield	3.7	%	ISO 527
Tensile Strain, break	4.7	%	ISO 527
Tensile Modulus, 1 mm/min	4460	MPa	ISO 527
Flexural Stress	129	MPa	ISO 178
Flexural Modulus	4100	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	88	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	8	cm-kgf/cm	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	166	cm-kgf	ASTM D 3763
Multiaxial Impact	73	cm-kgf	ISO 6603
Izod Impact, unnotched 80*10*4 +23°C	59	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	7	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	142	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	2	°C	ASTM D 648



LNP™ THERMOCOMP™ Compound DF0029ER

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
CTE, -40°C to 40°C, flow	5.04E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	5.94E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	5.E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	5.9E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	143	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	136	°C	ISO 75/Af
PHYSICAL			
Density	1.3	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.1	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.6 - 0.8	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	0.6 - 0.8	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs (5)	0.67	%	ISO 294
Mold Shrinkage, xflow, 24 hrs (5)	0.68	%	ISO 294
Density	1.3	g/cm ³	ISO 1183



LNP™ THERMOCOMP™ Compound DF0029ER

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120	°C
Drying Time	4	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	305 - 325	°C
Front - Zone 3 Temperature	320 - 330	°C
Middle - Zone 2 Temperature	310 - 320	°C
Rear - Zone 1 Temperature	295 - 305	°C
Mold Temperature	80 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm