



LNP™ THERMOCOMP™ Compound DF006

Americas: COMMERCIAL

Also known as: LNP™ THERMOCOMP™ Compound DF-1006

Product reorder name: DF006

LNP THERMOCOMP DF006 is a compound based on Polycarbonate resin containing 30% Glass Fiber.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	1160	kgf/cm ²	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	2.7	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	3.2	%	ASTM D 638
Tensile Modulus, 50 mm/min	88000	kgf/cm ²	ASTM D 638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	1510	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	83900	kgf/cm ²	ASTM D 790
Tensile Stress, break, 5 mm/min	114	MPa	ISO 527
Tensile Strain, break, 5 mm/min	7.5	%	ISO 527
Flexural Modulus, 2 mm/min	7860	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	93	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	14	cm-kgf/cm	ASTM D 256
Izod Impact, unnotched 80*10*4 +23°C	56	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	14	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	144	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	140	°C	ASTM D 648
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	145	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	141	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.45	-	ASTM D 792
Density	1.44	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.07	%	ASTM D 570
Density	1.45	g/cm ³	ISO 1183



LNP™ THERMOCOMP™ Compound DF006

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
PHYSICAL			
Moisture Absorption (23°C / 50% RH)	0.07	%	ISO 62



LNP™ THERMOCOMP™ Compound DF006

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120	°C
Drying Time	4	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	305 - 325	°C
Front - Zone 3 Temperature	320 - 330	°C
Middle - Zone 2 Temperature	310 - 320	°C
Rear - Zone 1 Temperature	295 - 305	°C
Mold Temperature	80 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm