



LNP™ THERMOCOMP™ Compound DF008

Americas: COMMERCIAL

Also known as: LNP™ THERMOCOMP™ Compound DF-1008

Product reorder name: DF008

LNP THERMOCOMP™ DF008 is a compound based on Polycarbonate resin containing 40% Glass Fiber.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	1430	kgf/cm ²	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	6.5	%	ASTM D 638
Tensile Modulus, 50 mm/min	228800	kgf/cm ²	ASTM D 638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	2090	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	117900	kgf/cm ²	ASTM D 790
Tensile Stress, break, 5 mm/min	132	MPa	ISO 527
Tensile Strain, break, 5 mm/min	6.9	%	ISO 527
Tensile Modulus, 1 mm/min	14350	MPa	ISO 527
Flexural Modulus, 2 mm/min	11190	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	73	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	15	cm-kgf/cm	ASTM D 256
Izod Impact, unnotched 80*10*4 +23°C	45	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	14	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	138	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	134	°C	ASTM D 648
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	141	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	140	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.12	-	ASTM D 792
Density	1.52	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.08	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	1 - 3	%	ASTM D 955



LNP™ THERMOCOMP™ Compound DF008

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
PHYSICAL			
Mold Shrinkage, xflow, 24 hrs (5)	0.3 - 0.5	%	ASTM D 955
Density	1.12	g/cm ³	ISO 1183
Moisture Absorption (23°C / 50% RH)	0.08	%	ISO 62



LNP™ THERMOCOMP™ Compound DF008

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120	°C
Drying Time	4	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	305 - 325	°C
Front - Zone 3 Temperature	320 - 330	°C
Middle - Zone 2 Temperature	310 - 320	°C
Rear - Zone 1 Temperature	295 - 305	°C
Mold Temperature	80 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm