



LNP™ THERMOCOMP™ COMPOUND DF00A8P

REGION ASIA

DESCRIPTION

LNP THERMOCOMP DF00A8P is a compound based on Polycarbonate resin containing Glass Fiber, Flame Retardant. Added features of this material include: High modulus, good flatness, good impact performance, Non-Brominated & Non-Chlorinated Flame Retardant.

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	154	MPa	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	2.1	%	ASTM D 638
Tensile Modulus, 5 mm/min	15320	MPa	ASTM D 638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	223	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	14870	MPa	ASTM D 790
Tensile Stress, break, 5 mm/min	153	MPa	ISO 527
Tensile Strain, break, 5 mm/min	1.9	%	ISO 527
Tensile Modulus, 1 mm/min	15130	MPa	ISO 527
IMPACT			
Izod Impact, unnotched, 23°C	520	J/m	ASTM D 4812
Izod Impact, notched, 23°C	127	J/m	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	21	J	ASTM D 3763
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	12	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	38	kJ/m ²	ISO 179/1eU
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	107	°C	ASTM D 648
PHYSICAL			
Density	1.635	g/cm ³	ASTM D 792
Mold Shrinkage, flow, 24 hrs (5)	0.05 – 0.2	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	0.05 – 0.2	%	ASTM D 955
Melt Volume Rate, MVR at 300°C/5.0 kg	28	cm ³ /10 min	ASTM D 1238
FLAME CHARACTERISTICS			
UL Recognized, 94V-0 Flame Class Rating (3)	1	mm	UL 94



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
INJECTION MOLDING			
Drying Temperature	110	°C	
Drying Time	3 – 6	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	285 – 310	°C	
Nozzle Temperature	285 – 305	°C	
Front - Zone 3 Temperature	280 – 300	°C	
Middle - Zone 2 Temperature	270 – 290	°C	
Rear - Zone 1 Temperature	260 – 280	°C	
Mold Temperature	80 – 110	°C	
Back Pressure	0.1 – 0.3	MPa	
Screw Speed	50 – 90	rpm	