



LNP™ THERMOCOMP™ Compound DX05475

Americas: COMMERCIAL

Also known as: LNP™ THERMOCOMP™ Compound DFA-113

Product reorder name: DX05475

LNP THERMOCOMP DX05474 is a compound based on Polycarbonate resin containing Glass Fiber. Added features of this material include: Flame Retardant.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yield	610	kgf/cm ²	ASTM D 638
Tensile Stress, break	550	kgf/cm ²	ASTM D 638
Tensile Strain, yield	4.9	%	ASTM D 638
Tensile Strain, break	8.2	%	ASTM D 638
Tensile Modulus, 50 mm/min	36600	kgf/cm ²	ASTM D 638
Flexural Stress	1050	kgf/cm ²	ASTM D 790
Flexural Modulus	36900	kgf/cm ²	ASTM D 790
IMPACT			
Izod Impact, unnotched, 23°C	108	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	5	cm-kgf/cm	ASTM D 256
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	132	°C	ASTM D 648
PHYSICAL			
Density	1.29	g/cm ³	ASTM D 792
Mold Shrinkage, flow, 24 hrs (5)	0.3 - 0.5	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	0.3 - 0.4	%	ASTM D 955



LNP™ THERMOCOMP™ Compound DX05475

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120	°C
Drying Time	4	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	305 - 325	°C
Front - Zone 3 Temperature	320 - 330	°C
Middle - Zone 2 Temperature	310 - 320	°C
Rear - Zone 1 Temperature	295 - 305	°C
Mold Temperature	80 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm