



LNP™ THERMOCOMP™ Compound DX10311X

Asia Pacific: COMMERCIAL

DX10311X is 30% glass fiber reinforced, impact modified polycarbonate resin. High flow and good ductility.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	1160	kgf/cm ²	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	2.5	%	ASTM D 638
Tensile Modulus, 5 mm/min	88600	kgf/cm ²	ASTM D 638
Flexural Stress	1830	kgf/cm ²	ASTM D 790
Flexural Modulus	75500	kgf/cm ²	ASTM D 790
Tensile Stress, break, 5 mm/min	115	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2.5	%	ISO 527
Tensile Modulus, 1 mm/min	8610	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	172	MPa	ISO 178
Flexural Stress, break, 2 mm/min	180	MPa	ISO 178
Flexural Modulus, 2 mm/min	7450	MPa	ISO 178
IMPACT			
Charpy Impact, unnotched, 23°C	45	kJ/m ²	ISO 179/2C
Izod Impact, unnotched, 23°C	72	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	16	cm-kgf/cm	ASTM D 256
Charpy Impact, notched, 23°C	17	kJ/m ²	ISO 179/2C
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	125	°C	ASTM D 648
CTE, -40°C to 40°C, flow	2.1E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	6.8E-05	1/°C	ASTM E 831
PHYSICAL			
Specific Gravity	1.43	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm (5)	0.1 - 0.4	%	SABIC Method
Mold Shrinkage, xflow, 3.2 mm (5)	0.2 - 0.5	%	SABIC Method



LNP™ THERMOCOMP™ Compound DX10311X

Asia Pacific: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
PHYSICAL Melt Volume Rate, MVR at 300°C/2.16 kg	9	cm ³ /10 min	ISO 1133



LNP™ THERMOCOMP™ Compound DX10311X

Asia Pacific: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	90 - 110	°C
Drying Time	3 - 5	hrs
Melt Temperature	280 - 320	°C
Nozzle Temperature	280 - 320	°C
Front - Zone 3 Temperature	280 - 320	°C
Middle - Zone 2 Temperature	280 - 320	°C
Rear - Zone 1 Temperature	250 - 280	°C
Mold Temperature	90 - 120	°C
Back Pressure	1 - 5	MPa
Screw Speed	30 - 100	rpm