



LNP™ THERMOCOMP™ Compound DZ004

Americas: COMMERCIAL

Also known as: LNP™ THERMOCOMP™ Compound DF-1004 M

Product reorder name: DZ004

LNP THERMOCOMP DZ004 is a compound based on Polycarbonate resin containing 20% Milled Glass.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, break	610	kgf/cm ²	ASTM D 638
Tensile Strain, break	4.5	%	ASTM D 638
Tensile Modulus, 50 mm/min	37700	kgf/cm ²	ASTM D 638
Flexural Stress	980	kgf/cm ²	ASTM D 790
Flexural Modulus	35700	kgf/cm ²	ASTM D 790
IMPACT			
Izod Impact, unnotched, 23°C	116	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	5	cm-kgf/cm	ASTM D 256
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	136	°C	ASTM D 648
PHYSICAL			
Density	1.41	g/cm ³	ASTM D 792
Mold Shrinkage, flow, 24 hrs (5)	0.3	%	ASTM D 955



LNP™ THERMOCOMP™ Compound DZ004

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120	°C
Drying Time	4	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	305 - 325	°C
Front - Zone 3 Temperature	320 - 330	°C
Middle - Zone 2 Temperature	310 - 320	°C
Rear - Zone 1 Temperature	295 - 305	°C
Mold Temperature	80 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm