

Lexan* Resin OQ1030

Americas: COMMERCIAL

Optical quality high flow, high purity PC resin for CD/DVD applications.

Property

TYPICAL PROPERTIES ⁽¹⁾			
MECHANICAL	Value	Unit	Standard
Tensile Stress, yld, Type I, 50 mm/min	62	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	49	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	6	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	100	%	ASTM D 638
Tensile Modulus, 50 mm/min	2410	MPa	ASTM D 638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	93	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2240	MPa	ASTM D 790
Tensile Stress, yield, 50 mm/min	60	MPa	ISO 527
Tensile Stress, break, 50 mm/min	45	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	5	%	ISO 527
Tensile Strain, break, 50 mm/min	>50	%	ISO 527
Tensile Modulus, 1 mm/min	2300	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	90	MPa	ISO 178
Flexural Modulus, 2 mm/min	2400	MPa	ISO 178
Hardness, H358/30	100	MPa	ISO 2039-1
IMPACT	Value	Unit	Standard
Izod Impact, notched, 23°C	550	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	46	J	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	12	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	14	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	NB	kJ/m ²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*4 sp=62mm	NB	kJ/m ²	ISO 179/1eU
THERMAL	Value	Unit	Standard
Vicat Softening Temp, Rate B/50	140	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	132	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	120	°C	ASTM D 648
CTE, -40°C to 40°C, flow	8.1E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	7.2E-05	1/°C	ASTM E 831
CTE, 23°C to 80°C, flow	7.E 05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	7.E 05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	140	°C	ISO 306
Vicat Softening Temp, Rate B/120	142	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	135	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	122	°C	ISO 75/Ae
PHYSICAL	Value	Unit	Standard
Specific Gravity	1.2	-	ASTM D 792
Mold Shrinkage on Tensile Bar, flow (2)	0.05 - 0.07	%	SABIC Method

+135-3858-6433 (GuangDong)
+188-1699-6168 (ShangHai)
+852-6957-5415 (HongKong)

Mold Shrinkage, flow, 3.2 mm	0.6 - 0.8	%	SABIC Method
Melt Flow Rate, 250°C/1.2 kgf	12.8	g/10 min	ASTM D 1238
Density	1.19	g/cm ³	ISO 1183
Melt Volume Rate, MVR at 250°C/1.2 kg	13	cm ³ /10 min	ISO 1133

Processing

Parameter	Value	Unit
Injection Molding		
Drying Temperature	120	°C
Drying Time	3 - 4	hrs
Drying Time (Cumulative)	48	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	305 - 330	°C
Nozzle Temperature	305 - 330	°C
Front - Zone 3 Temperature	305 - 330	°C
Middle - Zone 2 Temperature	295 - 320	°C
Rear - Zone 1 Temperature	280 - 310	°C
Mold Temperature	65 - 95	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	60 - 200	rpm

THESE PROPERTY VALUES ARE NOT INTENDED FOR SPECIFICATION PURPOSES.

(1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured after at least 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume and melt flow rates, are measured on injection molded samples. All samples tested under ISO test standards are prepared according to ISO 294.

(2) Only typical data for selection purposes. Not to be used for part or tool design.

(3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

(4) Internal measurements according to UL standards.