



CYCOLOY™ Resin C2950HF
Americas: COMMERCIAL

Non-chlorinated and non-brominated flame retardant PC/ABS offering balanced impact and heat properties plus improved flow for various applications.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	650	kgf/cm ²	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	5	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	40	%	ASTM D 638
Flexural Stress, yld, 2.6 mm/min, 100 mm span	980	kgf/cm ²	ASTM D 790
Flexural Modulus, 2.6 mm/min, 100 mm span	26300	kgf/cm ²	ASTM D 790
Hardness, Rockwell R	121	-	ASTM D 785
IMPACT			
Izod Impact, notched, 23°C	46	cm-kgf/cm	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	553	cm-kgf	ASTM D 3763
THERMAL			
Vicat Softening Temp, Rate B/50	112	°C	ASTM D 1525
HDT, 1.82 MPa, 3.2mm, unannealed	87	°C	ASTM D 648
HDT, 0.45 MPa, 6.4 mm, unannealed	101	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	93	°C	ASTM D 648
CTE, -30°C to 30°C, flow	7.2E-05	1/°C	ASTM D 696
CTE, -30°C to 30°C, xflow	7.2E-05	1/°C	ASTM D 696
Thermal Conductivity	0.2	W/m-°C	ASTM C 177
Relative Temp Index, Elec	85	°C	UL 746B
Relative Temp Index, Mech w/impact	85	°C	UL 746B
Relative Temp Index, Mech w/o impact	85	°C	UL 746B
PHYSICAL			
Specific Gravity	1.18	-	ASTM D 792
Water Absorption, 24 hours	0.1	%	ASTM D 570
Water Absorption, equilibrium, 23C	0.4	%	ASTM D 570



CYCOLOY™ Resin C2950HF

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
PHYSICAL			
Mold Shrinkage, flow, 3.2 mm (5)	0.4 - 0.6	%	SABIC Method
Mold Shrinkage, xflow, 3.2 mm (5)	0.4 - 0.6	%	SABIC Method
Melt Flow Rate, 260°C/2.16 kgf	22	g/10 min	ASTM D 1238
ELECTRICAL			
Volume Resistivity	1.6E+17	Ohm-cm	ASTM D 257
Surface Resistivity	>1.E+16	Ohm	ASTM D 257
Dielectric Strength, in oil, 3.2 mm	24.3	kV/mm	ASTM D 149
Relative Permittivity, 50/60 Hz	2.8	-	ASTM D 150
Relative Permittivity, 1 MHz	2.7	-	ASTM D 150
Dissipation Factor, 50/60 Hz	0.0052	-	ASTM D 150
Dissipation Factor, 1 MHz	0.0071	-	ASTM D 150
Arc Resistance, Tungsten {PLC}	6	PLC Code	ASTM D 495
Hot Wire Ignition {PLC}	2	PLC Code	UL 746A
High Voltage Arc Track Rate {PLC}	3	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	0	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	2	PLC Code	UL 746A
FLAME CHARACTERISTICS			
UL Recognized, 94V-2 Flame Class Rating (3)	0.76	mm	UL 94
UL Recognized, 94V-0 Flame Class Rating (3)	1.49	mm	UL 94
UL Recognized, 94-5VA Rating (3)	3.4	mm	UL 94
UL Recognized, 94-5VB Rating (3)	2.48	mm	UL 94
Oxygen Index (LOI)	30	%	ASTM D 2863



CYCOLOY™ Resin C2950HF

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80 - 90	°C
Drying Time	3 - 4	hrs
Drying Time (Cumulative)	8	hrs
Maximum Moisture Content	0.04	%
Melt Temperature	245 - 275	°C
Nozzle Temperature	245 - 275	°C
Front - Zone 3 Temperature	245 - 275	°C
Middle - Zone 2 Temperature	220 - 265	°C
Rear - Zone 1 Temperature	220 - 255	°C
Mold Temperature	60 - 80	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	40 - 70	rpm
Shot to Cylinder Size	30 - 80	%
Vent Depth	0.038 - 0.076	mm