



LNP™ LUBRICOMP™ Compound Cycloyol_C2801

Americas: COMMERCIAL

LNP™; LUBRICOMP™; CYCOLOY_C2801 compound is a 5% PTFE reinforced PC+ABS, wear resistant, flame retardant compound for moving components in business equipment. Medium heat performance

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	630	kgf/cm ²	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	520	kgf/cm ²	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	110	%	ASTM D 638
Flexural Stress, yld, 2.6 mm/min, 100 mm span	970	kgf/cm ²	ASTM D 790
Flexural Modulus, 2.6 mm/min, 100 mm span	27700	kgf/cm ²	ASTM D 790
K-factor xE-10, PV=2000 psi-fpm vs Steel	430	-	SABIC Method
Coefficient of Friction on steel, Static	0.16	-	ASTM D 1894
Coefficient of Friction on steel, Kinetic	0.21	-	ASTM D 1894
IMPACT			
Izod Impact, notched, 23°C	13	cm-kgf/cm	ASTM D 256
THERMAL			
HDT, 1.82 MPa, 6.4 mm, unannealed	82	°C	ASTM D 648
Relative Temp Index, Elec	60	°C	UL 746B
Relative Temp Index, Mech w/impact	60	°C	UL 746B
Relative Temp Index, Mech w/o impact	60	°C	UL 746B
PHYSICAL			
Specific Gravity	1.22	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm (5)	0.4 - 0.5	%	SABIC Method
Mold Shrinkage, xflow, 3.2 mm (5)	0.3 - 0.5	%	SABIC Method
ELECTRICAL			
Hot Wire Ignition {PLC}	3	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	0	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	1	PLC Code	UL 746A
FLAME CHARACTERISTICS			
UL Recognized, 94V-0 Flame Class Rating (3)	1.49	mm	UL 94
UL Recognized, 94-5VB Rating (3)	2.48	mm	UL 94



LNP™ LUBRICOMP™ Compound Cycloyol_C2801

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	75 - 80	°C
Drying Time	3 - 4	hrs
Drying Time (Cumulative)	8	hrs
Maximum Moisture Content	0.04	%
Melt Temperature	230 - 275	°C
Nozzle Temperature	230 - 275	°C
Front - Zone 3 Temperature	225 - 275	°C
Middle - Zone 2 Temperature	215 - 260	°C
Rear - Zone 1 Temperature	210 - 255	°C
Mold Temperature	50 - 70	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	40 - 70	rpm
Shot to Cylinder Size	30 - 80	%
Vent Depth	0.038 - 0.076	mm