



LNP™ STAT-LOY™ Compound NX13401

Americas: COMMERCIAL

Also known as: LNP™ STAT-LOY™ Compound NX13401

Product reorder name: NX13401

LNP STAT-LOY NX13401 is a compound based on PC+ABS blend. Added features of this material include: Antistat, Flame Retardant, Excellent Release.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	450	kgf/cm ²	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	380	kgf/cm ²	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	4.2	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	55.7	%	ASTM D 638
Tensile Modulus, 5 mm/min	20900	kgf/cm ²	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	680	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	19100	kgf/cm ²	ASTM D 790
Tensile Stress, yield, 5 mm/min	44	MPa	ISO 527
Tensile Stress, break, 5 mm/min	37	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	4	%	ISO 527
Tensile Strain, break, 5 mm/min	23	%	ISO 527
Tensile Modulus, 1 mm/min	1840	MPa	ISO 527
Flexural Stress	63	MPa	ISO 178
Flexural Modulus, 2 mm/min	1750	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	84	cm-kgf/cm	ASTM D 256
Multiaxial Impact	371	cm-kgf	ISO 6603
Instrumented Impact Total Energy, 23°C	392	cm-kgf	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	26	kJ/m ²	ISO 180/1U
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	95	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	80	°C	ASTM D 648
CTE, -30°C to 30°C, flow	8.5E-05	1/°C	ASTM D 696



LNP™ STAT-LOY™ Compound NX13401

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
CTE, -30°C to 30°C, xflow	9.3E-05	1/°C	ASTM D 696
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	85	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	75	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.23	-	ASTM D 792
Density	1.23	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.6	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.3 - 0.5	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	0.4 - 0.6	%	ASTM D 955
Moisture Absorption (23°C / 50% RH)	0.9	%	ISO 62
ELECTRICAL			
Surface Resistivity	1.E+09 - 1.E+11	Ohm	ASTM D 257



LNP™ STAT-LOY™ Compound NX13401

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	200 - 230	°C
Front - Zone 3 Temperature	220 - 230	°C
Middle - Zone 2 Temperature	210 - 220	°C
Rear - Zone 1 Temperature	200 - 210	°C
Mold Temperature	40 - 55	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm