



LNP™ VERTON™ Compound NV008E

Americas: COMMERCIAL

Also known as: LNP™ VERTON™ Compound PCA-F-7008 EM

Product reorder name: NV008E

LNP VERTON NV008E is a compound based on PC+ABS resin containing 40% Long Glass Fiber. Added features of this material include: Easy Molding. Structural.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yield	1490	kgf/cm ²	ASTM D 638
Tensile Stress, break	1490	kgf/cm ²	ASTM D 638
Tensile Strain, yield	1.4	%	ASTM D 638
Tensile Strain, break	1.4	%	ASTM D 638
Tensile Modulus, 50 mm/min	206600	kgf/cm ²	ASTM D 638
Flexural Stress	2170	kgf/cm ²	ASTM D 790
Flexural Modulus	112400	kgf/cm ²	ASTM D 790
Tensile Stress, yield	156	MPa	ISO 527
Tensile Stress, break	156	MPa	ISO 527
Tensile Strain, yield	1.3	%	ISO 527
Tensile Strain, break	1.3	%	ISO 527
Tensile Modulus, 1 mm/min	12400	MPa	ISO 527
Flexural Stress	224	MPa	ISO 178
Flexural Modulus	11700	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	75	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	31	cm-kgf/cm	ASTM D 256
Izod Impact, notched, -40°C	32	cm-kgf/cm	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	143	cm-kgf	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	50	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	28	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -40°C	34	kJ/m ²	ISO 180/1A



LNP™ VERTON™ Compound NV008E

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
CTE, -40°C to 40°C, flow	1.98E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	4.32E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	2.06E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	4.47E-05	1/°C	ISO 11359-2
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	131	°C	ISO 75/Af
PHYSICAL			
Density	1.49	g/cm ³	ASTM D 792
Mold Shrinkage, xflow, 24 hrs (5)	0.3	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs (5)	0.05	%	ISO 294
Mold Shrinkage, xflow, 24 hrs (5)	0.27	%	ISO 294
Density	1.5	g/cm ³	ISO 1183



LNP™ VERTON™ Compound NV008E

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80 - 95	°C
Drying Time	2 - 4	hrs
Maximum Moisture Content	0.04	%
Melt Temperature	275 - 290	°C
Front - Zone 3 Temperature	280 - 295	°C
Middle - Zone 2 Temperature	270 - 280	°C
Rear - Zone 1 Temperature	260 - 270	°C
Mold Temperature	60 - 95	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm