



GELOY™ RESIN HRA222

REGION AMERICAS

DESCRIPTION

PC/ASA flame retardant, excellent weatherability.

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	63	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	56	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	4.3	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	> 100	%	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	4.2	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	> 100	%	ASTM D 638
Tensile Stress, break, 50 mm/min	45	MPa	ISO 527
Tensile Strain, break, 5 mm/min	> 50	%	ISO 527
Tensile Strain, break, 50 mm/min	> 50	%	ISO 527
Tensile Modulus, 1 mm/min	2520	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	93	MPa	ISO 178
Flexural Modulus, 2 mm/min	2510	MPa	ISO 178
IMPACT			
Izod Impact, notched 80*10*4 +23°C	17	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 0°C	12	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	9	kJ/m ²	ISO 180/1A
THERMAL			
CTE, -30°C to 80°C, flow	6.9E-05	1/°C	ISO 11359-2
Ball Pressure Test, 75°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate A/50	111	°C	ISO 306
Vicat Softening Temp, Rate B/50	102	°C	ISO 306
Vicat Softening Temp, Rate B/120	104	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	99	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	88	°C	ISO 75/Ae
PHYSICAL			
Density	1.17	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.6	%	ISO 62



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Moisture Absorption (23°C / 50% RH)	0.2	%	ISO 62
Melt Volume Rate, MVR at 260°C/2.16 kg	13	cm³/10 min	ISO 1133