



LNP™ LUBRICOMP™ Compound PDXF89080

Americas: COMMERCIAL

Also known as: LNP™ LUBRICOMP™ Compound PDX-F-89080

Product reorder name: PDXF89080

LNP LUBRICOMP PDXF89080 is a compound based on Polyethylene containing Proprietary Fillers. Added feature of this grade is: Wear Resistant.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	100	kgf/cm ²	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	90	kgf/cm ²	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	73	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	90	%	ASTM D 638
Tensile Modulus, 5 mm/min	2000	kgf/cm ²	ASTM D 638
Flexural Modulus, 1.3 mm/min, 50 mm span	1200	kgf/cm ²	ASTM D 790
Tensile Stress, yield, 5 mm/min	9	MPa	ISO 527
Tensile Stress, break, 5 mm/min	8	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	88	%	ISO 527
Tensile Strain, break, 5 mm/min	164	%	ISO 527
Tensile Modulus, 1 mm/min	240	MPa	ISO 527
Flexural Stress	5	MPa	ISO 178
Flexural Modulus, 2 mm/min	120	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	NB	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	30	cm-kgf/cm	ASTM D 256
Multiaxial Impact	193	cm-kgf	ISO 6603
Instrumented Impact Total Energy, 23°C	197	cm-kgf	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	37	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	42	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	23	°C	ASTM D 648



LNP™ LUBRICOMP™ Compound PDXF89080

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
CTE, -30°C to 30°C, flow	2.08E-04	1/°C	ASTM D 696
CTE, -30°C to 30°C, xflow	1.99E-04	1/°C	ASTM D 696
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	41	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	23	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	0.92	-	ASTM D 792
Density	0.92	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.03	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	2 - 4	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	1 - 3	%	ASTM D 955
Moisture Absorption (23°C / 50% RH)	0.03	%	ISO 62



LNP™ LUBRICOMP™ Compound PDXF89080

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Melt Temperature	230	°C
Front - Zone 3 Temperature	220 - 230	°C
Middle - Zone 2 Temperature	210 - 220	°C
Rear - Zone 1 Temperature	195 - 205	°C
Mold Temperature	40 - 55	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm