



LNP™ THERMOCOMP™ Compound LC006EXQ

Americas: COMMERCIAL

Also known as: LNP™ THERMOCOMP™ Compound LC006EXQ

Product reorder name: LC006EXQ

LNP THERMOCOMP LC006EXQ is a compound based on Polyetheretherketone containing 30% Carbon Fiber. Added features of this material include: Electrically Conductive, Easy Molding.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	3200	kgf/cm ²	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	1.7	%	ASTM D 638
Tensile Modulus, 5 mm/min	323200	kgf/cm ²	ASTM D 638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	4860	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	276300	kgf/cm ²	ASTM D 790
Tensile Stress, break, 5 mm/min	319	MPa	ISO 527
Tensile Strain, break, 5 mm/min	1.5	%	ISO 527
Tensile Modulus, 1 mm/min	35320	MPa	ISO 527
Flexural Stress	457	MPa	ISO 178
Flexural Modulus, 2 mm/min	27230	MPa	ISO 178
Shear Strength	1213	kgf/cm ²	ASTM C 273
Shear Modulus	48490	kgf/cm ²	ASTM C 273
IMPACT			
Izod Impact, unnotched, 23°C	95	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	7	cm-kgf/cm	ASTM D 256
Instrumented Impact Total Energy, 23°C	68	cm-kgf	ASTM D 3763
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	332	°C	ASTM D 648
CTE, -40°C to 150°C, flow	5.E-06	1/°C	ASTM E 831
CTE, -40°C to 150°C, xflow	3.E-05	1/°C	ASTM E 831
PHYSICAL			
Specific Gravity	1.4	-	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.05	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.15 - 0.3	%	ASTM D 955



LNP™ THERMOCOMP™ Compound LC006EXQ

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
PHYSICAL			
Mold Shrinkage, xflow, 24 hrs (5)	0.7 - 1.4	%	ASTM D 955
ELECTRICAL			
Surface Resistivity	1.E+03 - 1.E+04	Ohm	ASTM D 257



LNP™ THERMOCOMP™ Compound LC006EXQ

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	150	°C
Drying Time	4 - 6	hrs
Front - Zone 3 Temperature	380 - 400	°C
Middle - Zone 2 Temperature	380 - 400	°C
Rear - Zone 1 Temperature	370 - 380	°C
Mold Temperature	175 - 190	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	60 - 100	rpm