



LNP™ STAT-KON™ Compound EX02598C

Americas: COMMERCIAL

Also known as: LNP™ STAT-KON™ Compound PDX-E-02598 CCS

Product reorder name: EX02598C

LNP STAT-KON EX02598C is a compound based on Polyetherimide containing Proprietary Filler(s). Added features of this material include: Clean Compound System, Electrically Conductive.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	530	kgf/cm ²	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	1.7	%	ASTM D 638
Tensile Modulus, 5 mm/min	34700	kgf/cm ²	ASTM D 638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	990	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	33700	kgf/cm ²	ASTM D 790
Tensile Stress, break, 5 mm/min	60	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2.1	%	ISO 527
Tensile Modulus, 1 mm/min	3240	MPa	ISO 527
Flexural Stress	72	MPa	ISO 178
Flexural Modulus, 2 mm/min	3110	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	27	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	1	cm-kgf/cm	ASTM D 256
Multiaxial Impact	9	cm-kgf	ISO 6603
Instrumented Impact Total Energy, 23°C	28	cm-kgf	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	18	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	2	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	172	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	163	°C	ASTM D 648
CTE, -30°C to 30°C, flow	5.E-05	1/°C	ASTM D 696
CTE, -30°C to 30°C, xflow	5.4E-05	1/°C	ASTM D 696
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	171	°C	ISO 75/Bf



LNP™ STAT-KON™ Compound EX02598C

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	160	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.27	-	ASTM D 792
Density	1.26	g/cm³	ASTM D 792
Mold Shrinkage, flow, 24 hrs (5)	0.6 - 0.8	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	0.7 - 0.9	%	ASTM D 955
ELECTRICAL			
Surface Resistivity	3.E+00 - 6.E+00	Ohm	ASTM D 257



LNP™ STAT-KON™ Compound EX02598C

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120 - 150	°C
Drying Time	4 - 6	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	360 - 365	°C
Front - Zone 3 Temperature	365 - 375	°C
Middle - Zone 2 Temperature	355 - 365	°C
Rear - Zone 1 Temperature	345 - 355	°C
Mold Temperature	120 - 150	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	60 - 100	rpm