



ULTEM™ RESIN 1010P

REGION AMERICAS

DESCRIPTION

Enhanced flow Polyetherimide (Tg 217C) in 350 micron powder. ECO Conforming.

TYPICAL PROPERTY VALUES

Revision 20180906

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	110	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	110	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	7	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	60	%	ASTM D 638
Tensile Modulus, 5 mm/min	3580	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	3585	MPa	ASTM D 790
Flexural Stress, yld, 2.6 mm/min, 100 mm span	165	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	3500	MPa	ASTM D 790
Hardness, Rockwell M	109	-	ASTM D 785
Taber Abrasion, CS-17, 1 kg	10	mg/1000cy	ASTM D 1044
Tensile Stress, yield, 5 mm/min	105	MPa	ISO 527
Tensile Stress, break, 5 mm/min	85	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	6	%	ISO 527
Tensile Strain, break, 5 mm/min	60	%	ISO 527
Tensile Modulus, 1 mm/min	3200	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	160	MPa	ISO 178
Flexural Modulus, 2 mm/min	3300	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	1335	J/m	ASTM D 4812
Izod Impact, notched, 23°C	32	J/m	ASTM D 256
Izod Impact, notched, -30°C	30	J/m	ASTM D 256
Izod Impact, Reverse Notched, 3.2 mm	1174	J/m	ASTM D 256
Gardner, 23°C	33	J	ASTM D 3029
Instrumented Impact Total Energy, 23°C	38	J	ASTM D 3763
Izod Impact, notched 80*10*4 +23°C	NB	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	NB	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	5	kJ/m ²	ISO 179/1eA
THERMAL			
Vicat Softening Temp, Rate B/50	211	°C	ASTM D 1525
HDT, 1.82 MPa, 3.2mm, unannealed	190	°C	ASTM D 648
HDT, 0.45 MPa, 6.4 mm, unannealed	207	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	198	°C	ASTM D 648
CTE, -40°C to 40°C, xflow	5.5E-05	1/°C	ASTM E 831
CTE, -20°C to 150°C, flow	5.5E-05	1/°C	ASTM E 831
Thermal Conductivity	0.22	W/m-°C	ASTM C177

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
CTE, -40°C to 40°C, flow	5.5E-05	1 / °C	ISO 11359-2
CTE, -40°C to 40°C, xflow	5.5E-05	1 / °C	ISO 11359-2
Ball Pressure Test, 75°C +/- 2°C	Passes	-	IEC 60695-10-2
Vicat Softening Temp, Rate B/50	211	°C	ISO 306
Vicat Softening Temp, Rate B/120	212	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	190	°C	ISO 75 /Af
PHYSICAL			
Specific Gravity	1.27	-	ASTM D 792
Water Absorption, 24 hours	0.25	%	ASTM D 570
Water Absorption, equilibrium, 23C	1.25	%	ASTM D 570
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.7	%	SABIC method
Melt Flow Rate, 337°C/6.6 kgf	17.8	g/10 min	ASTM D 1238
Density	1.27	g/cm³	ISO 1183
Water Absorption, (23°C/sat)	1.25	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.7	%	ISO 62
Melt Volume Rate, MVR at 340°C/5.0 kg	13	cm³/10 min	ISO 1133
ELECTRICAL			
Volume Resistivity	1.E+17	Ohm-cm	ASTM D 257
Dielectric Strength, in air, 1.6 mm	32.6	kV/mm	ASTM D 149
Dielectric Strength, in oil, 1.6 mm	27.9	kV/mm	ASTM D 149
Relative Permittivity, 1 kHz	3.15	-	ASTM D 150
Dissipation Factor, 1 kHz	0.0013	-	ASTM D 150
Dissipation Factor, 2450 MHz	0.0025	-	ASTM D 150
FLAME CHARACTERISTICS			
Oxygen Index (LOI)	44	%	ASTM D 2863
INJECTION MOLDING			
Drying Temperature	150	°C	
Drying Time	4 – 6	hrs	
Drying Time (Cumulative)	24	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	350 – 400	°C	
Nozzle Temperature	345 – 400	°C	
Front - Zone 3 Temperature	345 – 400	°C	
Middle - Zone 2 Temperature	340 – 400	°C	
Rear - Zone 1 Temperature	330 – 400	°C	
Mold Temperature	135 – 165	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.