



ULTEM™ RESIN HU2210

REGION AMERICAS

DESCRIPTION

20% Glass fiber filled, enhanced flow Polyetherimide (Tg 217°C). ECO Conforming. For medical devices and pharmaceutical applications. Healthcare management of change, biocompatible (ISO 10993 or USP Class VI); food contact compliant; Steam, Gamma, EtO, and E-beam sterilizable.

TYPICAL PROPERTY VALUES

Revision 20180906

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	139	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	140	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	4	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	4	%	ASTM D 638
Tensile Modulus, 5 mm/min	6890	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	227	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	6890	MPa	ASTM D 790
Tensile Stress, yield, 5 mm/min	140	MPa	ISO 527
Tensile Stress, break, 5 mm/min	140	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	5	%	ISO 527
Tensile Strain, break, 5 mm/min	5	%	ISO 527
Tensile Modulus, 1 mm/min	6800	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	210	MPa	ISO 178
Flexural Modulus, 2 mm/min	6500	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	475	J/m	ASTM D 4812
Izod Impact, notched, 23°C	64	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	13	J	ASTM D 3763
Izod Impact, notched 80*10*4 +23°C	5	kJ/m²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	5	kJ/m²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	8	kJ/m²	ISO 179/1eA
THERMAL			
Vicat Softening Temp, Rate B/50	226	°C	ASTM D 1525
HDT, 1.82 MPa, 6.4 mm, unannealed	211	°C	ASTM D 648
CTE, -40°C to 40°C, flow	2.5E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	5.E-05	1/°C	ASTM E 831
Vicat Softening Temp, Rate B/50	212	°C	ISO 306
Vicat Softening Temp, Rate B/120	218	°C	ISO 306
PHYSICAL			
Specific Gravity	1.42	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.3 – 0.5	%	SABIC method
Melt Flow Rate, 337°C/6.6 kgf	8.4	g/10 min	ASTM D 1238
Density	1.42	g/cm³	ISO 1183
Water Absorption, (23°C/sat)	1	%	ISO 62



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Moisture Absorption (23°C / 50% RH)	0.55	%	ISO 62
INJECTION MOLDING			
Drying Temperature	150	°C	
Drying Time	4 – 6	hrs	
Drying Time (Cumulative)	24	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	350 – 400	°C	
Nozzle Temperature	345 – 400	°C	
Front - Zone 3 Temperature	345 – 400	°C	
Middle - Zone 2 Temperature	340 – 400	°C	
Rear - Zone 1 Temperature	330 – 400	°C	
Mold Temperature	135 – 165	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.