

EXTEMTM RESIN XH2315

REGION ASIA

DESCRIPTION

Extem XH2315 Resin. Also UL rating V094 at 0.75 and V0,5VA at 1.0 and 1.5-1.65

TYPICAL PROPERTY VALUES

Revision 20181122

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	156	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	156	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	3	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	3	%	ASTM D 638
Tensile Modulus, 5 mm/min	10230	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	206	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	8960	MPa	ASTM D 790
Tensile Stress, yield, 5 mm/min	147	MPa	ISO 527
Tensile Stress, break, 5 mm/min	147	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	2	%	ISO 527
Tensile Strain, break, 5 mm/min	2	%	ISO 527
Tensile Modulus, 1 mm/min	10530	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	200	MPa	ISO 178
Flexural Modulus, 2 mm/min	9000	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	86	J/m	ASTM D 256
Izod Impact, Reverse Notched, 3.2 mm	320	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	8	J	ASTM D 3763
Izod Impact, notched 80°10°4 +23°C	5	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80°10°4 sp=62mm	24	kJ/m ²	ISO 179/1eA
THERMAL			
Vicat Softening Temp, Rate B/50	267	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	257	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	254	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	255	°C	ASTM D 648
CTE, 23°C to 150°C, flow	1.6E-05	1/°C	ASTM E 831
CTE, 23°C to 150°C, xflow	5.3E-05	1/°C	ASTM E 831
PHYSICAL			
Specific Gravity	1.52	-	ASTM D 792
Water Absorption, 23°C/48hrs	0.59	%	ASTM D 570
Melt Flow Rate, 367°C/6.6 kgf	4	g/10 min	ASTM D 1238
Density	1.52	g/cm ³	ISO 1183
INJECTION MOLDING			
Drying Temperature	175	°C	



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Drying Time	4 – 6	hrs	
Drying Time (Cumulative)	24	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	380 – 405	°C	
Nozzle Temperature	375 – 400	°C	
Front - Zone 3 Temperature	380 – 405	°C	
Middle - Zone 2 Temperature	370 – 395	°C	
Rear - Zone 1 Temperature	360 – 380	°C	
Mold Temperature	150 – 175	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	70 – 100	rpm	
Shot to Cylinder Size	40 – 70	%	
Vent Depth	0.025 – 0.076	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.