



LNP™ LUBRICOMP™ Compound JCL36

Europe-Africa-Middle East: COMMERCIAL

LNP LUBRICOMP JCL36 is a compound based on Polyethersulfone resin containing Carbon Fiber, PTFE. Added features include : Internally Lubricated, Electrically Conductive.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, break, 5 mm/min	142	MPa	ISO 527
Tensile Strain, break, 5 mm/min	1.7	%	ISO 527
Tensile Modulus, 1 mm/min	19300	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	218	MPa	ISO 178
Flexural Modulus, 2 mm/min	17000	MPa	ISO 178
IMPACT			
Izod Impact, unnotched 80*10*4 +23°C	25	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	7	kJ/m ²	ISO 180/1A
THERMAL			
CTE, 23°C to 60°C, flow	7.E-06	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	3.6E-05	1/°C	ISO 11359-2
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	223	°C	ISO 75/Af
PHYSICAL			
Mold Shrinkage, flow (5)	0.5	%	SABIC Method
Density	1.54	g/cm ³	ISO 1183
ELECTRICAL			
Surface Resistivity	1.E+02 - 1.E+03	Ohm	ASTM D 257
FLAME CHARACTERISTICS			
UL Recognized, 94V-0 Flame Class Rating (3)	1.5	mm	UL 94



LNP™ LUBRICOMP™ Compound JCL36
Europe-Africa-Middle East: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120 - 150	°C
Drying Time	4	hrs
Maximum Moisture Content	0.05	%
Melt Temperature	355 - 370	°C
Front - Zone 3 Temperature	370 - 380	°C
Middle - Zone 2 Temperature	360 - 370	°C
Rear - Zone 1 Temperature	345 - 355	°C
Mold Temperature	140 - 150	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	60 - 100	rpm