

FORTIFY™ ELASTOMER C05075DF

POLYOLEFIN ELASTOMER

DESCRIPTION

FORTIFY™ Polyolefin Elastomer (POE) C05075DF is an ethylene octene copolymer produced by solution polymerization using metallocene catalyst. This product is available as free flowing pellets.

FORTIFY™ Polyolefin Elastomer (POE) C05075DF is a grade typically used in foam application. This grade is designed as a low density and high performance copolymer modifier to provide superior resilience and compression set properties.

TYPICAL APPLICATIONS

SABIC® FORTIFY™ C05075DF can be typically used for all types of foam, produced with chemical blowing agents or physical gases, X-linked and non Xlinked. The main applications are: Footwear, Sports & Leisure, Packaging, Building & Construction, Automotive.

Contact SABIC for detailed information about this resin and its applications. This product is not intended for and must not be used in any pharmaceutical/medical applications.

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Density	868	kg/m ³	ASTM D792
Melt Flow Rate (MFR)			
at 190°C and 2.16 kg	0.5	g/10 min	ASTM D1238
at 230°C and 2.16 kg	0.9	g/10 min	ASTM D1238
Mooney viscosity			
ML 1+4, 121 °C	36	MU	ASTM D1646
MECHANICAL PROPERTIES ⁽¹⁾			
Tensile Properties			
strength at break	10.3	MPa	ASTM D638
elongation	800	%	ASTM D638
100% modulus	3.1	MPa	ASTM D638
Durometer Hardness			
shore A (1 second)	74	-	ASTM D2240
shore D (1 second)	23	-	ASTM D2240
Flexural Modulus (1% Secant)	15.2	MPa	ASTM D790 A
Tear Strength (Type C)	45.1	kN/m	ASTM D624
THERMAL PROPERTIES			
Peak Melting Temperature	59	°C	SABIC method
Glass Transition Temperature, Tg	-54	°C	SABIC method

(1) All physical properties were measured from specimens cut from compression molded. These typical values depend on manufacturing conditions. Therefore, customers should confirm the product performance by using their own tests.