+135-3858-6433 (GuangDong) +188-1699-6168 (ShangHai) +852-6957-5415 (HongKong)



# FORTIFYTM ELASTOMER C1055D

## POLYOLEFIN ELASTOMER

### **DESCRIPTION**

SABIC® FORTIFY™ C1055D is an ethylene octene copolymer. This product is available as free flowing pellets.

SABIC® FORTIFY™ C1055D is designed as a low density and high performance copolymer modifier to provide superior impact properties and flow characteristics.

#### **TYPICAL APPLICATIONS**

Impact modifier in thermoplastic olefin compounds, footwear midsoles and wire and cable extrusion.

### **TYPICAL PROPERTY VALUES**

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Density	857	kg/m³	ASTM D792
Melt Flow Rate (MFR)			
at 190°C and 2.16 kg	1.0	g/10 min	ASTM D1238
at 230°C and 2.16 kg	2.2	g/10 min	ASTM D1238
Mooney viscosity			
ML 1+4, 121 °C	24	MU	ASTM D1646
MECHANICAL PROPERTIES (1)			
Tensile Properties			
strength at break	3.1	MPa	ASTM D638
elongation	>1000	%	ASTM D638
100% modulus	1.4	MPa	ASTM D638
Durometer Hardness			
shore A (1 second)	55	-	ASTM D2240
shore D (1 second)	12	-	ASTM D2240
Flexural Modulus (1% Secant)	4.4	MPa	ASTM D790 A
Tear Strength (Type C)	27.5	kN/m	ASTM D624
THERMAL PROPERTIES			
	37	°C	SABIC method
Peak Melting Temperature	31	C	SADIC MELITOD

<sup>(1)</sup> All physical properties were measured from specimens cut from compression molded. These typical values depend on manufacturing conditions. Therefore, customers should confirm the product performance by using their own tests.