+135-3858-6433 (GuangDong) +188-1699-6168 (ShangHai) +852-6957-5415 (HongKong)



## FORTIFYTM ELASTOMER C13060

## **DESCRIPTION**

FORTIFY<sup>TM</sup> Polyolefin Elastomer (POE) C13060 is an ethylene octene copolymer produced by solution polymerization using metallocene catalyst. This product is available as free flowing pellets.

FORTIFY<sup>TM</sup> Polyolefin Elastomer (POE) C13060 is designed as allow density and high performance copolymer modifier to provide superior impact properties and flow characteristics.

## **TYPICAL APPLICATIONS**

Impact modifier in thermoplastic olefin compounds, footwear midsoles and wire and cable extrusion.

## **TYPICAL PROPERTY VALUES**

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Density	863	kg/m³	ASTM D792
Melt Flow Rate (MFR)			
at 190°C and 2.16 kg	13.0	g/10 min	ASTM D1238
at 230°C and 2.16 kg	27.0	g/10 min	ASTM D1238
Mooney viscosity			
ML 1+4, 121 °C	3	MU	ASTM D1646
MECHANICAL PROPERTIES (1)			
Tensile Properties			
strength at break	3.1	MPa	ASTM D638
1 2			
elongation	>1000	%	ASTM D638
eiongation 100% modulus	>1000	% MPa	ASTM D638 ASTM D638
100% modulus			
100% modulus  Durometer Hardness	1.8	MPa	ASTM D638
100% modulus  Durometer Hardness shore A (1 second)	1.8	MPa -	ASTM D638
100% modulus  Durometer Hardness shore A (1 second) shore D (1 second)	1.8 63 16	MPa	ASTM D638  ASTM D2240  ASTM D2240
100% modulus  Durometer Hardness shore A (1 second) shore D (1 second)  Flexural Modulus (1% Secant)	1.8 63 16 7.5	MPa - - MPa	ASTM D638  ASTM D2240  ASTM D2240  ASTM D790 A
100% modulus  Durometer Hardness  shore A (1 second)  shore D (1 second)  Flexural Modulus (1% Secant)  Tear Strength (Type C)	1.8 63 16 7.5	MPa - - MPa	ASTM D638  ASTM D2240  ASTM D2240  ASTM D790 A

<sup>(1)</sup> All physical properties were measured from specimens cut from compression molded. These typical values depend on manufacturing conditions. Therefore, customers should confirm the product performance by using their own tests.