

# FORTIFY™ ELASTOMER C30070D

## POLYOLEFIN ELASTOMER

### DESCRIPTION

FORTIFY™ Polyolefin Elastomer (POE) C30070D is an ethylene octene copolymer produced by solution polymerization using metallocene catalyst. This product is available as free flowing pellets.

FORTIFY™ Polyolefin Elastomer (POE) C30070D is designed as a high performance copolymer modifier to provide superior toughness, softness and optical properties. It also provides excellent flow properties.

### TYPICAL APPLICATIONS

Impact modifier in thermoplastic olefin compounds, footwear midsoles and wire and cable extrusion.

### TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES</b>			
Density	868	kg/m <sup>3</sup>	ASTM D792
<b>Melt Flow Rate (MFR)</b>			
at 190°C and 2.16 kg	30.0	g/10 min	ASTM D1238
at 230°C and 2.16 kg	70.0	g/10 min	ASTM D1238
<b>Mooney viscosity</b>			
ML 1+4, 121 °C	2	MU	ASTM D1646
<b>MECHANICAL PROPERTIES <sup>(1)</sup></b>			
<b>Tensile Properties</b>			
strength at break	3.1	MPa	ASTM D638
elongation	>1000	%	ASTM D638
1% secant modulus	10.8	MPa	ASTM D638
100% modulus	1.7	MPa	ASTM D638
<b>Durometer Hardness</b>			
shore A (1 second)	68	-	ASTM D2240
shore D (1 second)	17	-	ASTM D2240
Flexural Modulus (1% Secant)	10.8	MPa	ASTM D790 A
Tear Strength (Type C)	29.4	kN/m	ASTM D624
<b>THERMAL PROPERTIES</b>			
Peak Melting Temperature	62	°C	SABIC method
Glass Transition Temperature, Tg	-52	°C	SABIC method

(1) All physical properties were measured from specimens cut from compression molded. These typical values depend on manufacturing conditions. Therefore, customers should confirm the product performance by using their own tests.