+135-3858-6433 (GuangDong) +188-1699-6168 (ShangHai) +852-6957-5415 (HongKong)



# FORTIFYTM ELASTOMER C5075DP

# POLYOLEFIN ELASTOMER

### **DESCRIPTION**

FORTIFY<sup>TM</sup> Polyolefin Elastomer (POE) C5075DP is an ethylene octene copolymer produced by solution polymerization using metallocene catalyst. This product is available as free flowing pellets. This grade is designed as a low density and high performance copolymer, it provides excellent electrical properties, high transmittance and weathering resistance.

#### TYPICAL APPLICATIONS

- Photovoltaic encapsulation
- Impact modification
- Thermoplastic olefins

# **TYPICAL PROPERTY VALUES**

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES (1)			
Density	873	kg/m³	ASTM D792
Melt Flow Rate (MFR)		3,	
at 190°C and 2.16 kg	5	g/10 min	ASTM D1238
at 230°C and 2.16 kg	11	g/10 min	ASTM D1238
Mooney viscosity			
ML 1+4, 121 °C	8	MU	ASTM D1646
MECHANICAL PROPERTIES (2)			
Hardness			
Durometer Hardness, Shore A (1 second)	75	-	ASTM D2240
Durometer Hardness, Shore D (1 second)	22	-	ASTM D2240
Tensile Properties			
strength at break	8.0	MPa	ASTM D638
elongation	>800	%	ASTM D638
100% modulus	3.0	MPa	ASTM D638
Flexural Modulus (1% Secant)	12	MPa	ASTM D790 A
Tear Strength (Type C)	35	kN/m	ASTM D624
THERMAL PROPERTIES			
Peak Melting Temperature	69	°C	SABIC method
Glass Transition Temperature, Tg	-54	°C	SABIC method
ELECTRICAL PROPERTIES			
Volume resistivity	>10E+16	Ω.cm	SABIC method

<sup>(1)</sup> Typical values; not to be construed as specification limits

<sup>(2)</sup> All physical properties were measured from specimens cut from compression molded. These typical values depend on manufacturing conditions. Therefore, customers should confirm the product performance by using their own tests.