



SABIC® FORTIFY C1070D

POLYOLEFIN ELASTOMER

DESCRIPTION

SABIC® FORTIFY™ C1070D is an ethylene octene copolymer produced by solution polymerization using metallocene catalyst. This product is available as free flowing pellets.

SABIC® FORTIFY™ C1070D is designed as a low density and high performance copolymer modifier to provide superior impact properties and flow characteristics.

TYPICAL APPLICATIONS

Impact modification in thermoplastic olefin compounds, injection molded industrial and consumer durable goods, wire and cable and footwear.

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Density	868	kg/m ³	ASTM D792
Melt Flow Rate			
at 190°C and 2.16 kg	1.0	g/10 min	ASTM D1238
at 230°C and 2.16 kg	2.0	g/10 min	ASTM D1238
Mooney viscosity (ML 1+4, 121 °C)	22	MU	ASTM D1646
MECHANICAL PROPERTIES			
Durometer Hardness			
shore A (1 second)	71	-	ASTM D2240
shore D (1 second)	21	-	ASTM D2240
Flexural Modulus (1% Secant)	13.2	MPa	ASTM D790 A
Tear Strength (Type C)	39.2	kN/m	ASTM D624
FILM PROPERTIES			
Tensile Properties ⁽¹⁾			
stress at break	9.3	MPa	ASTM D638
elongation	850	%	ASTM D638
100% modulus	2.9	MPa	ASTM D638
THERMAL PROPERTIES			
Peak Melting Temperature	62	°C	SABIC method
Glass Transition Temperature, T_g	-52	°C	SABIC method