+135-3858-6433 (GuangDong) +188-1699-6168 (ShangHai) +852-6957-5415 (HongKong)



SABIC[®] FORTIFY[™] C13060D

POLYOLEFIN ELASTOMER

DESCRIPTION

SABIC[®] FORTIFY[™] C13060D is an ethylene octene copolymer produced by solution polymerization using metallocene catalyst. This product is available as free flowing pellets.

SABIC® FORTIFY C13060D is designed as allow density and high performance copolymer modifier to provide superior impact properties and flow characteristics.

TYPICAL APPLICATIONS

Impact modifier in thermoplastic olefin compounds, footwear midsoles and wire and cable extrusion.

TYPICAL PROPERTY VALUES

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|-----------------------------------|----------------|----------|--------------|
| POLYMER PROPERTIES | | | |
| Density | 863 | kg/m³ | ASTM D792 |
| Melt Flow Rate | | | |
| at 190°C and 2.16 kg | 13.0 | g/10 min | ASTM D1238 |
| at 230°C and 2.16 kg | 27.0 | g/10 min | ASTM D1238 |
| Mooney viscosity (ML 1+4, 121 °C) | 3 | MU | ASTM D1646 |
| MECHANICAL PROPERTIES | | | |
| Tensile Properties | | | |
| strength at break | 2.3 | MPa | ASTM D638 |
| elongation | >1000 | % | ASTM D638 |
| 100% modulus | 1.8 | MPa | ASTM D638 |
| Durometer Hardness | | | |
| shore A (1 second) | 63 | - | ASTM D2240 |
| shore D (1 second) | 13 | - | ASTM D2240 |
| Flexural Modulus (1% Secant) | 7.5 | MPa | ASTM D790 A |
| Tear Strength (Type C) | 25.5 | kN/m | ASTM D624 |
| THERMAL PROPERTIES | | | |
| Peak Melting Temperature | 42 | °C | SABIC method |
| Glass Transition Temperature, Tg | -56 | °C | SABIC method |