+135-3858-6433 (GuangDong) +188-1699-6168 (ShangHai) +852-6957-5415 (HongKong)



# SABIC® FORTIFY C3080

# POLYOLEFIN ELASTOMER

# **DESCRIPTION**

SABIC<sup>®</sup> FORTIFY<sup>TM</sup> C3080 is an ethylene octene copolymer produced by solution polymerization using metallocene catalyst. This product is available as free flowing pellets.

SABIC® FORTIFY  $^{\text{TM}}$  C3080 is designed as a high performance copolymer modifier to provide superior toughness, softness and optical properties. It provides excellent flow properties too.

# **TYPICAL APPLICATIONS**

Typical applications are impact modifier in thermoplastic olefin compounds, footwear midsoles and wire and cable extrusion.

# TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Density	880	kg/m³	ASTM D792
Melt Flow Rate			
at 190°C and 2.16 kg	3.0	g/10 min	ASTM D1238
at 230°C and 2.16 kg	6.0	g/10 min	ASTM D1238
Mooney viscosity (ML 1+4, 121 °C)	11	MU	ASTM D1646
MECHANICAL PROPERTIES (1)			
Tensile Properties			
stress at break	11.8	MPa	ASTM D638
elongation	900	%	ASTM D638
100% modulus	3.3	MPa	ASTM D638
Durometer Hardness			
shore A (1 second)	78	-	ASTM D2240
shore D (1 second)	24	-	ASTM D2240
Flexural Modulus (1% Secant)	19.6	MPa	ASTM D790 A
Tear Strength (Type C)	41.2	kN/m	ASTM D624
THERMAL PROPERTIES			
Peak Melting Temperature	68	°C	SABIC method
Glass Transition Temperature, Tg	-49	°C	SABIC method