



LNP™ LUBRICOMP™ Compound KFL32R

Americas: COMMERCIAL

Also known as: LNP™ LUBRICOMP™ Compound KFL-4032 ER

Product reorder name: KFL32R

LNP LUBRICOMP™ KFL32R is a compound based on Acetal Copolymer resin containing 10% Glass Fiber, 15% PTFE. Added feature of this material is: Easy Release, Wear Resistant.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, break	810	kgf/cm ²	ASTM D 638
Tensile Strain, break	2.6	%	ASTM D 638
Tensile Modulus, 50 mm/min	52000	kgf/cm ²	ASTM D 638
Flexural Stress	1180	kgf/cm ²	ASTM D 790
Flexural Modulus	49200	kgf/cm ²	ASTM D 790
Tensile Stress, break	79	MPa	ISO 527
Tensile Strain, break	2.5	%	ISO 527
Tensile Modulus, 1 mm/min	5400	MPa	ISO 527
Flexural Stress	122	MPa	ISO 178
Flexural Modulus	5800	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	35	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	4	cm-kgf/cm	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	69	cm-kgf	ASTM D 3763
Multiaxial Impact	17	cm-kgf	ISO 6603
Izod Impact, unnotched 80*10*4 +23°C	26	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	5	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	165	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	161	°C	ASTM D 648
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	162	°C	ISO 75/Af
PHYSICAL			
Density	1.56	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.18	%	ASTM D 570



LNP™ LUBRICOMP™ Compound KFL32R

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
PHYSICAL			
Mold Shrinkage, flow, 24 hrs (5)	1.1	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	1.3	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs (5)	1.08	%	ISO 294
Mold Shrinkage, xflow, 24 hrs (5)	1.34	%	ISO 294
Density	1.56	g/cm ³	ISO 1183
Moisture Absorption (23°C / 50% RH)	0.33	%	ISO 62



LNP™ LUBRICOMP™ Compound KFL32R

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Melt Temperature	200 - 215	°C
Front - Zone 3 Temperature	210 - 220	°C
Middle - Zone 2 Temperature	195 - 205	°C
Rear - Zone 1 Temperature	175 - 190	°C
Mold Temperature	80 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm