



LNP™ STAT-LOY™ Compound KX09024

Europe-Africa-Middle East: COMMERCIAL

Also known as: LNP™ STAT-LOY™ Compound KX09024
Product reorder name: KX09024

LNP STAT-LOY KX09024 is a compound based on Polyacetal with reduced Resistivity. Added features include: Antistatic Properties

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Strain, break, 5 mm/min	12	%	ISO 527
Tensile Modulus, 1 mm/min	1000	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	48	MPa	ISO 178
Flexural Modulus, 2 mm/min	1400	MPa	ISO 178
IMPACT			
Izod Impact, notched 80*10*4 +23°C	9	kJ/m ²	ISO 180/1A
THERMAL			
CTE, 23°C to 60°C, flow	1.44E-04	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	1.59E-04	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	136	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	67	°C	ISO 75/Af
PHYSICAL			
Mold Shrinkage, flow (5)	2.8	%	SABIC Method
Density	1.27	g/cm ³	ISO 1183
ELECTRICAL			
Volume Resistivity	1.E+08 - 1.E+10	Ohm-cm	ASTM D 257
Surface Resistivity	1.E+08 - 1.E+10	Ohm	ASTM D 257



LNP™ STAT-LOY™ Compound KX09024
Europe-Africa-Middle East: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Melt Temperature	195 - 205	°C
Front - Zone 3 Temperature	200 - 210	°C
Middle - Zone 2 Temperature	190 - 200	°C
Rear - Zone 1 Temperature	175 - 190	°C
Mold Temperature	70 - 95	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm