



LNP* Thermocomp* Compound KF-1006

Asia Pacific: COMMERCIAL

LNP* Thermocomp* KF-1006 is a compound based on Acetal Copolymer resin containing Glass Fiber.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	UNIT	STANDARD
MECHANICAL			
Tensile Stress, break	1320	kgf/cm ²	ASTM D 638
Tensile Strain, break	2.3	%	ASTM D 638
Tensile Modulus, 50 mm/min	107500	kgf/cm ²	ASTM D 638
Flexural Stress	1960	kgf/cm ²	ASTM D 790
Flexural Modulus	97700	kgf/cm ²	ASTM D 790
IMPACT			
Izod Impact, unnotched, 23°C	73	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	9	cm-kgf/cm	ASTM D 256
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	162	°C	ASTM D 648
PHYSICAL			
Density	1.64	g/cm ³	ASTM D 792
Mold Shrinkage, flow, 24 hrs	0.3	%	ASTM D 955