



SABIC[®] COHERE[™] S100L

METALLOCENE POLYOLEFIN PLASTOMER

DESCRIPTION

SABIC[®] COHERE[™] S100L is an ethylene-octene copolymers produced via solution polymerization using advanced metallocene catalyst. It performs well in high performance flexible packaging applications with excellent toughness, hot tack, hot seal, optical properties and enhanced packaging integrity to reduce loss/waste. It contains slip and antiblock additives.

TYPICAL APPLICATIONS

- Packaging with outstanding sealing performance (low seal initiation temperature, broad hot tack window, excellent seal through contamination).
- Packaging available for high speed form-fill-sealing machine.

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Density	903	kg/m ³	ASTM D792
Melt Flow Rate			
at 190°C and 2.16 kg	1.0	g/10 min	ASTM D1238
OPTICAL PROPERTIES			
Haze	4	%	ASTM D1003
FILM PROPERTIES			
Tensile Properties ⁽¹⁾			
stress at break, MD	46	MPa	ASTM D882
stress at break, TD	52	MPa	ASTM D882
strain at break, MD	550	%	ASTM D882
strain at break, TD	620	%	ASTM D882
1% secant modulus, MD	53	MPa	ASTM D882
1% secant modulus, TD	60	MPa	ASTM D882
Dart Impact Strength ⁽¹⁾			
Method A	>1000	g	ASTM D1709
Elmendorf Tear Strength ⁽¹⁾			
MD	10	g/μm	ASTM D1922
TD	17	g/μm	ASTM D1922
Sealing Initiation Temperature ⁽²⁾	78	°C	SABIC method
THERMAL PROPERTIES			
Melting Point	98	°C	SABIC method

(1) Properties have been measured by producing 40 μm film with 2.1 BUR, screw diameter 35mm, die diameter 100mm, die gap 1mm.

(2) Temperature at which 4 N/25.4mm heat seal strength is achieved.