+135-3858-6433 (GuangDong) +188-1699-6168 (ShangHai) +852-6957-5415 (HongKong)



# SABIC® PPCOMPOUND 108CS20

## PP COMPOUND MINERAL FILLED IMPACT MODIFIED

# **DESCRIPTION**

SABIC<sup>®</sup> PPcompound 108CS20 is a material with good flow, impact and stiffness. The material is part of the SABIC<sup>®</sup> PP CS systems and also available as a CS system: using a mixture of 60% SABIC<sup>®</sup> PP 108MF10 and 40% SABIC<sup>®</sup> PPcompound 20MBT yields similar properties as listed below.

SABIC<sup>®</sup> PPcompound 108CS20 is a designated automotive grade.

IMDS ID: 111851732

## **TYPICAL PROPERTY VALUES**

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt flow rate (MFR)			
at 230 °C and 2.16 kg	7	dg/min	ISO 1133
Density <sup>(1)</sup>	1040	kg/m³	ISO 1183
Filler content	20	%	SABIC method
Mould shrinkage <sup>(2)</sup>			
24 hours after injection moulding	0.9	%	SABIC method
MECHANICAL PROPERTIES (1)			
Tensile test			
Tensile modulus	1500	MPa	ISO 527/1A
stress at yield	20	MPa	ISO 527/1A
stress at break	17	MPa	ISO 527/1A
strain at break	100	%	ISO 527/1A
Flexural test			
Flexural modulus	1500	MPa	ISO 178/1A
Izod impact notched <sup>(3)</sup>			
at 23 °C	N.B.	kJ/m²	ISO 180/1A
at 0 °C	25	kJ/m²	ISO 180/1A
at -20 °C	7	kJ/m²	ISO 180/1A
THERMAL PROPERTIES (1)			
Heat deflection temperature			
at 0.45 MPa (HDT/B)	110	°C	ISO 75
Coeff. of linear thermal expansion			
-30 °C to 100 °C	80	µm/mK	ISO 11359-2

<sup>(1)</sup> Injection molded sample ISO527-1A

#### **QUALITY**

SABIC is fully certified in accordance with the internationally accepted quality standard ISO9001.

<sup>(2)</sup> Injection molded plaque 65x65x3.2mm

<sup>(3)</sup> N.B.: No Break