



# SABIC<sup>®</sup> PP 108MF10

PP SUPER HIGH IMPACT

## DESCRIPTION

SABIC<sup>®</sup> PP 108MF10 is a super high impact copolymer which exhibits an unmatched cold impact resistance, high flow and excellent paint adhesion characteristics. Because of this unique and well balanced property profile our customers commonly use this material for painted car bumpers.

SABIC<sup>®</sup> PP 108MF10 is a designated automotive grade.

IMDS ID: 80775790

## TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES</b>			
<b>Melt Flow Rate</b>			
at 230 °C and 2.16 kg	10	dg/min	ISO 1133
<b>Density</b>	905	kg/m <sup>3</sup>	ISO 1183
<b>Mould shrinkage <sup>(1)</sup></b>			
24 hours after injection moulding	1.5	%	SABIC method
<b>FORMULATION</b>			
<b>Anti static agent</b>	<input type="checkbox"/>	-	-
<b>Nucleating agent</b>	<input checked="" type="checkbox"/>	-	-
<b>MECHANICAL PROPERTIES</b>			
<b>Tensile test</b>			
stress at yield <sup>(2)</sup>	19	MPa	ISO 527-2 1A
strain at yield	8	%	ISO 527-2 1A
Tensile modulus <sup>(3)</sup>	1000	MPa	ISO 527-2 1A
<b>Izod impact notched</b>			
at 23 °C	No Break	kJ/m <sup>2</sup>	ISO 180/1A
at 0 °C	No Break	kJ/m <sup>2</sup>	ISO 180/1A
at -20 °C	35	kJ/m <sup>2</sup>	ISO 180/1A
<b>Charpy Impact Strength Notched</b>			
at 23 °C	No Break	kJ/m <sup>2</sup>	ISO 179/1eA
at 0 °C	No Break	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Charpy impact unnotched</b>			
at 23 °C	No Break	kJ/m <sup>2</sup>	ISO 179/1eU
<b>Hardness Shore D</b>	52	-	ISO 868
<b>THERMAL PROPERTIES</b>			
<b>Vicat Softening Temperature <sup>(4)</sup></b>			
at 10 N (VST/A)	130	°C	ISO 306
at 50 N (VST/B)	50	°C	ISO 306