



SABIC[®] PP 49MK45

POLYPROPYLENE IMPACT COPOLYMER FOR INJECTION MOLDING

DESCRIPTION

SABIC[®] PP 49MK45 is specially developed for producing injection molded articles. This grade contains nucleating & antistatic agents. It has medium flow properties and excellent impact - stiffness balance.

TYPICAL APPLICATIONS

SABIC[®] PP 49MK45 can be used for housewares, furniture, toys, appliances, pails & containers.

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES ⁽¹⁾			
Melt Flow Rate			
@ 230°C & 2.16kg load	21	g/10 min	ASTM D 1238
Density at 23°C	905	kg/m ³	ASTM D1505
MECHANICAL PROPERTIES			
Tensile Properties			
Strength @ Yield	29	ppm	ASTM D 638
Elongation @ Yield	5	%	ISO 527-1/-2
Flexural Modulus (1% Secant)	1400	MPa	ASTM D790 A
Notched Izod Impact Strength at 23°C	65	J/m	ASTM D256
Notched Izod Impact Strength at -20°C	35	J/m	ASTM D256
Rockwell Hardness, R-Scale	95	-	ASTM D785
THERMAL PROPERTIES			
Vicat Softening Point	150	°C	ASTM D1525
Heat Deflection Temperature at 455kPa	106	°C	ASTM D648

(1) Typical values, not to be construed as specific limits

PROCESSING CONDITIONS

Barrel temperature range: 200 - 250°C Mold Shrinkage: 1.2 - 2.0% depending on wall thickness and processing conditions. Mold Temperature: Normally 15 - 40°C, up to 65°C for thick parts.

HEALTH, SAFETY AND FOOD CONTACT REGULATIONS

Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site <http://www.SABIC.com>. For additional specific information please contact SABIC local representative.

DISCLAIMER: This product is not intended for and must not be used in any pharmaceutical / medical applications.

STORAGE AND HANDLING

Polypropylene resin should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably do not exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PP resin within 6 months after delivery.