



SABIC[®] PP 501P

PP HOMOPOLYMER

DESCRIPTION

SABIC[®] PP 501P is a multi purpose grade for extrusion applications. Application:SABIC[®] PP 501P is typically used (by our customers) for extrusion of tapes and strapping. Health, Safety and Food Contact regulations: Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate			
at 230 °C and 2.16 kg	1.0	dg/min	ISO 1133
Density	905	kg/m ³	ASTM D1505
Molecular Weight Distribution	Broad	-	-
Isotacticity	Medium	-	-
FORMULATION			
Gas fading stabilized	<input type="checkbox"/>	-	SABIC method
MECHANICAL PROPERTIES			
Tensile test			
stress at yield	37	MPa	ISO 527-2 1A
strain at yield	10	%	ISO 527-2 1A
tensile modulus	1550	MPa	ISO 527-2 1A
THERMAL PROPERTIES			
Vicat Softening Temperature			
at 50 N (VST/B)	88	°C	ISO 306
at 10 N (VST/A)	152	°C	ISO 306

QUALITY

SABIC Europe is fully certified in accordance with the internationally accepted quality standard ISO9001.