

SABIC® PP 528K

POLYPROPYLENE HOMOPOLYMER FOR THERMOFORMING

DESCRIPTION

SABIC® PP 528K is formulated with an advanced agent and is specially developed for in-line and off-line thermoforming applications.

PP 528K encompasses the following features: high stiffness, good clarity, very good dimensional stability, easy process ability and faster cycling.

TYPICAL APPLICATIONS

SABIC® PP 528K is used for the production of containers mainly for food and health drink products such as cups, trays and lids.

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate at 230°C and 2.16kg	3	g/10 min	ASTM D1238
Density at 23°C	905	kg/m ³	ASTM D792
MECHANICAL PROPERTIES⁽¹⁾			
Tensile Properties			
Strength @ Yield	37	MPa	ASTM D 638
Elongation @ Yield	10	%	ASTM D 638
Flexural Modulus (1% Secant)	1700	MPa	ASTM D790 A
Izod Impact Strength			
notched, at 23°C	35	J/m	ASTM D256
Rockwell Hardness, R-Scale	102	-	ASTM D785
THERMAL PROPERTIES			
Vicat Softening Temperature	150	°C	ASTM D1525
Heat deflection temperature			
at 455kPa	112	°C	ASTM D648

(1) Based on injection molded specimens