



SABIC[®] PP 77MK40T

POLYPROPYLENE IMPACT COPOLYMER
REGION ASIA

DESCRIPTION

SABIC[®] PP 77MK40T is a medium fluidity polypropylene impact copolymer with high impact strength and high stiffness. It contains nucleating & antistatic agents.

TYPICAL APPLICATIONS

SABIC[®] PP 77MK40T can be used for auto interior or exterior, home appliance parts, housewares and compounding.

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt flow rate (MFR)			
at 230°C and 2.16 kg	10	g/10 min	ISO 1133
Density	905	kg/m ³	ASTM D1505
MECHANICAL PROPERTIES			
Tensile Strength at Yield	25	MPa	ASTM D638
Flexural Modulus (1% Secant)	1250	MPa	ASTM D790 A
Charpy Impact Strength Notched ⁽¹⁾			
at 23 °C	11	kJ/m ²	ISO 179-1
at -20 °C	5	kJ/m ²	ISO 179-1
Rockwell Hardness			
R-scale	95	-	ISO 2039-2
THERMAL PROPERTIES			
Heat deflection temperature			
at 455kPa	90	°C	ISO 75-2

(1) Based on injection molded specimens.