

SABIC[®] PP 90910

PP SUPER HIGH IMPACT

DESCRIPTION

SABIC[®] PP 90910 is a reactor-elastomer-modified material which offers a good cold impact resistance in combination with high flow. It is a highly attractive alternative to non-filled compounds and is typically used for painted car bumpers and exterior trim.

SABIC[®] PP 90910 is a designated automotive grade.

IMDS ID: 80775790

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate			
at 230 °C and 2.16 kg	22	dg/min	ISO 1133
Density	900	kg/m ³	ISO 1183
Mould shrinkage ⁽¹⁾			
24 hours after injection moulding	1.6	%	SABIC method
FORMULATION			
Anti static agent	☐	-	-
Nucleating agent	☒	-	-
MECHANICAL PROPERTIES			
Tensile test			
stress at yield	18	MPa	ISO 527-2 1A
strain at yield ⁽²⁾	8	%	ISO 527-2 1A
tensile modulus ⁽³⁾	850	MPa	ISO 527-2 1A
Izod impact notched			
at 23 °C	No Break	kJ/m ²	ISO 180/1A
at 0 °C	No Break	kJ/m ²	ISO 180/1A
at -20 °C	15	kJ/m ²	ISO 180/1A
Charpy Impact Strength Notched			
at 23 °C	No Break	kJ/m ²	ISO 179/1eA
at 0 °C	No Break	kJ/m ²	ISO 179/1eA
at -20 °C	No Break	kJ/m ²	ISO 179/1eA
Charpy impact unnotched			
at 23 °C	No Break	kJ/m ²	ISO 179/1eU
Hardness Shore D	50	-	ISO 868
THERMAL PROPERTIES			
Vicat Softening Temperature ⁽⁴⁾			
at 10 N (VST/A)	125	°C	ISO 306
at 50 N (VST/B)	49	°C	ISO 306