



# SABIC<sup>®</sup> PP FPC100

## PP IMPACT COPOLYMER FLOWPACT

### DESCRIPTION

SABIC<sup>®</sup> PP FPC100 has been developed as a new member of the SABIC<sup>®</sup> PP FLOWPACT range dedicated to the thin wall packaging market. It is nucleated and is characterized by a high crystallization temperature and excellent flow behaviour in combination with a nice stiffness to impact balance.

This grade is typically used for high-speed injection moulding and it enables very cost efficient processing on the basis of easy mould filling and very short cycle times. It has a very good antistatic performance and permitseasy demoulding. This material is typically used in thin wall packing applications both for food and non-food segments. This includes yellow fats/margarine tubs, dairy packaging and housewares. The grade has an excellent dimensional stability what is crucial for the thin wall packaging market.

### TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES</b>			
<b>Melt Flow Rate</b>			
at 230 °C and 2.16 kg	100	dg/min	ISO 1133
<b>Density</b>	905	kg/m <sup>3</sup>	ASTM D1505
<b>FORMULATION</b>			
<b>Anti static agent</b>	☑	-	-
<b>Nucleating agent</b>	☑	-	-
<b>MECHANICAL PROPERTIES</b>			
<b>Tensile test</b>			
stress at yield	25	MPa	ISO 527-2 1A
strain at yield <sup>(1)</sup>	4	%	ISO 527-2 1A
tensile modulus <sup>(2)</sup>	1600	MPa	ISO 527-2 1A
<b>Izod impact notched</b>			
at 0 °C	4	kJ/m <sup>2</sup>	ISO 180/1A
at 23 °C	5.5	kJ/m <sup>2</sup>	ISO 180/1A
<b>Charpy Impact Strength Notched</b>			
at 23 °C	8	kJ/m <sup>2</sup>	ISO 179/1eA
at 0 °C	6	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Hardness Shore D</b>	62	-	ISO 868
<b>THERMAL PROPERTIES</b>			
<b>Heat deflection temperature <sup>(3)</sup></b>			
at 0.45 MPa (HDT/B)	95	°C	ISO 75
at 1.80 MPa (HDT/A)	55	°C	ISO 75
<b>Vicat Softening Temperature <sup>(4)</sup></b>			
at 10 N (VST/A)	150	°C	ISO 306
at 50 N (VST/B)	76	°C	ISO 306