



LNP™ STAT-KON™ Compound MD000XXZ

Americas: COMMERCIAL

Also known as: LNP™ STAT-KON™ Compound M-2

Product reorder name: MD000XXZ

LNP™ STAT-KON MD000XXZ is a compound based on Polypropylene containing Carbon. Added feature of this grade is: Electrically Conductive.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	320	kgf/cm ²	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	240	kgf/cm ²	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	5.7	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	11	%	ASTM D 638
Tensile Modulus, 5 mm/min	20800	kgf/cm ²	ASTM D 638
Flexural Modulus, 1.3 mm/min, 50 mm span	17700	kgf/cm ²	ASTM D 790
Tensile Stress, yield, 5 mm/min	30	MPa	ISO 527
Tensile Stress, break, 5 mm/min	26	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	5	%	ISO 527
Tensile Strain, break, 5 mm/min	2.6	%	ISO 527
Tensile Modulus, 1 mm/min	1720	MPa	ISO 527
Flexural Stress	40	MPa	ISO 178
Flexural Modulus, 2 mm/min	1610	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	168	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	46	cm-kgf/cm	ASTM D 256
Multiaxial Impact	360	cm-kgf	ISO 6603
Instrumented Impact Total Energy, 23°C	396	cm-kgf	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	135	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	24	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	104	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	57	°C	ASTM D 648

(1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured after at least 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume and melt flow rates, are measured on injection molded samples. All samples tested under ISO test standards are prepared according to ISO 294.

(2) Only typical data for selection purposes. Not to be used for part or tool design.

(3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

(4) Internal measurements according to UL standards.

(5) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(6) Needs hard coat to consistently pass 60 sec Vertical Burn.



LNP™ STAT-KON™ Compound MD000XXZ

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
CTE, -30°C to 30°C, flow	8.4E-05	1/°C	ASTM D 696
CTE, -30°C to 30°C, xflow	9.7E-05	1/°C	ASTM D 696
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	91	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	56	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.02	-	ASTM D 792
Density	1.018	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.02	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	2	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	1.9	%	ASTM D 955
Moisture Absorption (23°C / 50% RH)	0.03	%	ISO 62
ELECTRICAL			
Surface Resistivity	1.E+02 - 1.E+05	Ohm	ASTM D 257

(1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured after at least 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume and melt flow rates, are measured on injection molded samples. All samples tested under ISO test standards are prepared according to ISO 294.

(2) Only typical data for selection purposes. Not to be used for part or tool design.

(3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

(4) Internal measurements according to UL standards.

(5) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(6) Needs hard coat to consistently pass 60 sec Vertical Burn.



LNP™ STAT-KON™ Compound MD000XXZ

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Melt Temperature	225 - 250	°C
Front - Zone 3 Temperature	240 - 250	°C
Middle - Zone 2 Temperature	215 - 225	°C
Rear - Zone 1 Temperature	195 - 205	°C
Mold Temperature	30 - 50	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm

(1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured after at least 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume and melt flow rates, are measured on injection molded samples. All samples tested under ISO test standards are prepared according to ISO 294.

(2) Only typical data for selection purposes. Not to be used for part or tool design.
(3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.
(4) Internal measurements according to UL standards.
(5) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
(6) Needs hard coat to consistently pass 60 sec Vertical Burn.