



LNP™ THERMOTUF™ Compound MF0049I

Europe-Africa-Middle East: COMMERCIAL

LNP THERMOTUF MF0049I is a compound based on Polypropylene resin containing Glass Fiber, Flame Retardant. Added features include; Flame Retardant, Chemically Coupled.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yield, 5 mm/min	57	MPa	ISO 527
Tensile Strain, break, 5 mm/min	3.7	%	ISO 527
Tensile Modulus, 1 mm/min	5300	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	88	MPa	ISO 178
Flexural Modulus, 2 mm/min	4700	MPa	ISO 178
IMPACT			
Izod Impact, unnotched 80*10*4 +23°C	35	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	10	kJ/m ²	ISO 180/1A
THERMAL			
CTE, 23°C to 60°C, flow	3.2E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	1.18E-04	1/°C	ISO 11359-2
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	156	°C	ISO 75/Af
PHYSICAL			
Mold Shrinkage, flow (5)	0.34	%	SABIC Method
Density	1.37	g/cm ³	ISO 1183
FLAME CHARACTERISTICS			
UL Compliant, 94V-0 Flame Class Rating (3)(4)	1.6	mm	UL 94 by SABIC-IP



LNP™ THERMOTUF™ Compound MF0049I

Europe-Africa-Middle East: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Melt Temperature	225 - 250	°C
Front - Zone 3 Temperature	240 - 250	°C
Middle - Zone 2 Temperature	215 - 225	°C
Rear - Zone 1 Temperature	195 - 205	°C
Mold Temperature	30 - 50	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm