



SABIC® PP RELY 71EK71PS

PP IMPACT COPOLYMER

DESCRIPTION

This impact copolymer has a high molecular weight and is provided with a long-term heat stabilisation package. It exhibits high stiffness in combination with outstanding impact strength even at low temperatures. This material is used for extrusion of sewage pipe applications and can also be used for blow-moulding and sheet extrusion. Health, Safety and Food Contact regulations

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate			
at 230 °C and 2.16 kg	0.30	dg/min	ISO 1133
Density	905	kg/m ³	ASTM D1505
FORMULATION			
Anti static agent	☐	-	-
Nucleating agent	☒	-	-
MECHANICAL PROPERTIES			
Tensile test			
strain at yield ⁽¹⁾	8	%	ISO 527-2 1A
stress at yield	28	MPa	ISO 527-2 1A
tensile modulus ⁽²⁾	1450	MPa	ISO 527-2 1A
Izod impact notched			
at 0 °C	35	kJ/m ²	ISO 180/1A
at -20 °C	6	kJ/m ²	ISO 180/1A
Izod impact notched			
at 23 °C	No Break	kJ/m ²	ISO 180/1A
Charpy Impact Strength Notched			
at 23 °C	80	kJ/m ²	ISO 179/1eA
at 0 °C	20	kJ/m ²	ISO 179/1eA
at -20 °C	7	kJ/m ²	ISO 179/1eA
Charpy impact unnotched			
at 23 °C	No Break	kJ/m ²	ISO 179/1eU
Hardness Shore D	66	-	ISO 868
THERMAL PROPERTIES			



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Heat deflection temperature ⁽³⁾			
at 0.45 MPa (HDT/B)	95	°C	ISO 75
at 1.80 MPa (HDT/A)	55	°C	ISO 75
Vicat Softening Temperature ⁽⁴⁾			
at 10 N (VST/A)	156	°C	ISO 306
at 50 N (VST/B)	81	°C	ISO 306
OIT 200°C	> 100	min	EN 728

- (1) Speed of testing: 50 mm/min
 (2) Speed of testing: 1 mm/min
 (3) Flat wise (testbar 80*10*4mm)
 (4) Temperature rate: 120°C/h

QUALITY

SABIC Europe is fully certified in accordance with the internationally accepted quality standard ISO9001.