+135-3858-6433 (GuangDong) +188-1699-6168 (ShangHai) +852-6957-5415 (HongKong)



# SABIC® PPCOMPOUND 37T1020

### PP COMPOUND MINERAL FILLED

## **DESCRIPTION**

SABIC<sup>®</sup> PPcompound 37T1020 is a high flow copolymer with 20% talc, offering an excellent balance between stiffness and impact resistance. It has been specially developed for automotive interior parts such as column cladding and door panels.

 $\mathsf{SABIC}^{\circledR}$  PPcompound 37T1020 is a designated automotive grade.

IMDS ID: 16161338

# **TYPICAL PROPERTY VALUES**

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt flow rate (MFR)			
at 230 °C and 2.16 kg	13	dg/min	ISO 1133
Density <sup>(1)</sup>	1040	kg/m³	ISO 1183
Filler content	20	%	SABIC method
Mould shrinkage (2)			
24 hours after injection moulding	1	%	SABIC method
MECHANICAL PROPERTIES (1)			
Tensile			
Tensile modulus	2100	MPa	ISO 527/1A
stress at yield	28	MPa	ISO 527/1A
stress at break	25	MPa	ISO 527/1A
strain at break	45	%	ISO 527/1A
Flexural test			
Flexural modulus	2650	MPa	ISO 178/1A
Izod impact notched <sup>(3)</sup>			
at 23 °C	5.7	kJ/m²	ISO 180/1A
at 0 °C	3.5	kJ/m²	ISO 180/1A
at -20 °C	3	kJ/m²	ISO 180/1A
THERMAL PROPERTIES (1)			
Heat deflection temperature			
at 0.45 MPa (HDT/B)	110	°C	ISO 75
Coeff. of linear thermal expansion			
-30 °C to 100 °C	100	µm/mK	ISO 11359-2

<sup>(1)</sup> Injection molded sample ISO527-1A

### **QUALITY**

SABIC is fully certified in accordance with the internationally accepted quality standard ISO 9001.

<sup>(2)</sup> Injection molded plaque 65x65x3.2mm

<sup>(3)</sup> N.B.: No Break